

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
6 December 2001 (06.12.2001)

PCT

(10) International Publication Number
WO 01/92228 A2(51) International Patent Classification⁷: C07D 211/94,
405/12, 401/12, C08K 5/3435, C08F 4/00, C07D 217/26,
209/44, 241/08(74) Common Representative: CIBA SPECIALTY CHEM-
ICALS HOLDING INC.; Klybeckstrasse 141, CH-4057
Basel (CH).

(21) International Application Number: PCT/EP01/05668

(22) International Filing Date: 17 May 2001 (17.05.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00810461.4 26 May 2000 (26.05.2000) EP(71) Applicant (for all designated States except US): CIBA
SPECIALTY CHEMICALS HOLDING INC. [CH/CH];
Klybeckstrasse 141, CH-4057 Basel (CH).


(72) Inventors; and

(75) Inventors/Applicants (for US only): HAFNER, Andreas
[CH/CH]; Balkenweg 23, CH-4460 Gelterkinden (CH).
KIRNER, Hans, Jürg [DE/CH]; Wartenbergstrasse 35,
CH-4133 Pratteln (CH). SCHWARZENBACH, Franz
[CH/CH]; Neufeldstrasse 11, CH-4402 Frenkendorf
(CH). VAN DER SCHAAF, Paul, Adriaan [NL/CH];
Marsstrasse 17, CH-4123 Allschwil (CH). NESVADBA,
Peter [CH/CH]; Route des Pralettes 83A, CH-1723 Marly
(CH).(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK,
SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA,
ZW.(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished
upon receipt of that reportFor two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR THE SYNTHESIS OF AMINE ETHERS FROM SECONDARY AMINO OXIDES

(57) Abstract: An amine ether of formula (A) wherein a is 1 or 2; and when a is 1, E is E'; when a is 2, E is L; E' is C₁-C₃₆ alkyl; C₃-C₁₈ alkenyl; C₂-C₁₈ alkynyl; C₅-C₁₈ cycloalkyl; C₅-C₁₈ cycloalkenyl; a radical of a saturated or unsaturated aliphatic bicyclic or tricyclic hydrocarbon of 7 to 12 carbon atoms; C₂-C₇alkyl or C₃-C₇alkenyl substituted by halogen; C₇-C₁₅aralkyl or C₇-C₁₅ aralkyl substituted by C₁-C₄ alkyl or phenyl; or E' is a radical of formula (VII) as explained in claim 1; T' is tertiary C₄-C₁₈alkyl or phenyl, each of which are unsubstituted or substituted by halogen, OH, COOR₂₁ or C(O)-R₂₂; or T' is C₅-C₁₂cycloalkyl; C₅-C₁₂cycloalkyl which is interrupted by at least one O or -NR₁₈; a polycyclic alkyl radical having 7-18 carbon atoms, or the same radical which is interruptedby at least one O or -NR₁₈; or T' is -C(G₁)(G₂)-T''; or C₁-C₁₈alkyl or C₅-C₁₂cycloalkyl substituted by F(I)T'' is hydrogen, halogen, NO₂, cyano, or is a monovalent organic radical comprising 1-50 carbon atoms; or T'' and T' together form a divalent organic linking group completing, together with the hindered amine nitrogen atom and the quaternary carbon atom substituted by G₁ and G₂, an optionally substituted five- or six-membered ring structure; and all other residues are as defined in claim 1, are obtained in good yield from the corresponding N-oxyl hindered amine precursor by reaction with a hydrocarbon E₁-H or H-L-H in the presence of an organic hydroperoxide and a catalytic amount of copper or a copper compound. The products of present process find utility as polymerization regulators and/or light stabilizers for organic material.

WO 01/92228 A2

PROCESS FOR THE SYNTHESIS OF AMINE ETHERS FROM SECONDARY AMINO
OXIDES

The instant invention pertains to a process for preparing amine ethers, e.g. N-hydrocarbyloxy substituted hindered amine compounds, by the reaction of the corresponding N-oxyl intermediate with a hydrocarbon in presence of an organic hydroperoxide and a copper catalyst, and some novel compounds obtainable by this process. The compounds made by the instant process are particularly effective in the stabilization of polymer compositions against harmful effects of light, oxygen and/or heat; they are also useful as initiators or regulators for radical polymerization processes which provide homopolymers, random copolymers, block copolymers, multiblock copolymers, graft copolymers and the like, at enhanced rates of polymerization and enhanced monomer to polymer conversions.

4-Hydroxy-1-oxyl-2,2,6,6-tetramethylpiperidine and 4-oxo-1-oxyl-2,2,6,6-tetramethylpiperidine are described as scavengers for some carbon centered radicals (S. Nigam et al., J. Chem. Soc., Trans. Faraday Soc., 1976, (72), 2324 and by K.-D. Asmus et al., Int. J. Radiat. Biol., 1976, (29), 211).

D. H. R. Barton et al., Tetrahedron, 1996, (52), 10301 describe the formation of some N-alkoxy-2,2,6,6-tetramethylpiperidine derivatives in the reaction of hydrocarbons with iron(II) and iron(III) species, hydrogen peroxide and various coadditives in the presence of N-oxyl-2,2,6,6-tetramethylpiperidine (TEMPO).


Unites States Patent No 5,374,729 describes a process for the preparation of N-methoxy derivatives of hindered amines from the reaction of the corresponding N-oxyl compound with methyl radicals produced from dimethyl sulfoxide by decomposing aqueous hydrogen peroxide in presence of a metal salt or by thermal decomposition of di-tert.butyl peroxide.

United States Patent No. 4,921,962 describes a process for the formation of N-hydrocarbyloxy derivatives of sterically hindered amines in which a hindered amine or N-oxyl substituted hindered amine is reacted with a hydrocarbon solvent in the presence of a hydroperoxide and a molybdenum catalyst.

- 2 -

It has now been found that N-hydrocarbyloxy substituted sterically hindered amines can most suitably be prepared from the N-oxyl intermediate and a hydrocarbon in presence of an organic hydroperoxide and a copper catalyst. The process of the invention uses only catalytic quantities of copper and does not require high temperatures.

Thus, present invention pertains to a process for the preparation of an amine ether of the formula A





wherein

a is 1 or 2;

when a is 1, E is E'

when a is 2, E is L;


E' is C₁-C₃₆ alkyl; C₃-C₁₈ alkenyl; C₂-C₁₈ alkynyl; C₅-C₁₈ cycloalkyl; C₅-C₁₈ cycloalkenyl; a radical of a saturated or unsaturated aliphatic bicyclic or tricyclic hydrocarbon of 7 to 12 carbon atoms; C₂-C₇alkyl or C₃-C₇alkenyl substituted by halogen, C₁-C₈alkoxy or phenoxy; C₄-C₁₂heterocycloalkyl; C₄-C₁₂heterocycloalkenyl; C₇-C₁₅ aralkyl or C₄-C₁₂heteroaralkyl, each of which is unsubstituted or substituted by C₁-C₄ alkyl or phenyl; or E' is a radical of formula (VII) or (VIII)



Ar is C₆-C₁₀aryl or C₅-C₉heteroaryl;

X is phenyl, naphthyl or biphenyl, which are substituted by 1, 2, 3 or 4 D and optionally further substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino;

- 3 -

D is a group , a group C(O)-G₁₃ or a group C(O)-G₅-C(O)-G₁₃;

G₁ and G₂, independently of each other, are hydrogen, halogen, NO₂, cyano, -CONR₅R₆, -(R₉)COOR₄, -C(O)-R₇, -OR₈, -SR₈, -NHR₈, -N(R₁₈)₂, carbamoyl, di(C₁-C₁₈alkyl)carbamoyl, -C(=NR₅)(NHR₆), C₁-C₁₈alkyl; C₃-C₁₈alkenyl; C₃-C₁₈alkinyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₂-C₁₂heterocycloalkyl; C₁-C₁₈alkyl or C₃-C₁₈alkenyl or C₃-C₁₈alkinyl or C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₂-C₁₂heterocycloalkyl substituted by OH, halogen, NO₂, amino, cyano, carboxy, COOR₂₁, C(O)-R₂₂, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino or a group -O-C(O)-R₇; C₂-C₁₈alkyl which is interrupted by at least one O atom and/or NR₅ group; or are C₆-C₁₀aryl; or phenyl or naphthyl which are substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, halogen, cyano, hydroxy, carboxy, COOR₂₁, C(O)-R₂₂, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or G₁ and G₂ together with the linking carbon atom form a C₃-C₁₂cycloalkyl radical;

G₅ and G₆ are independently of each other H or CH₃;

G₉ is C₁-C₁₂alkylene or a direct bond;

G₁₃ is C₁-C₁₈alkyl;

G₁₄ is C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl, an acyl radical of an aliphatic or unsaturated aliphatic carboxylic or carbamic acid containing 2 to 18 carbon atoms, an acyl radical of a cycloaliphatic carboxylic or carbamic acid containing 7 to 12 carbon atoms, or acyl radical of an aromatic acid containing 7 to 15 carbon atoms;

G₅₅ is H, CH₃ or phenyl;

G₆₆ is -CN or a group of the formula -COOR₄ or -CONR₅R₆ or -CH₂-O-G₁₄;

L is alkylene of 1 to 18 carbon atoms, cycloalkylene of 5 to 8 carbon atoms, cycloalkenylene of 5 to 8 carbon atoms, alkenylene of 3 to 18 carbon atoms, alkylene of 1 to 12 carbon atoms substituted by phenyl or by phenyl substituted by alkyl of 1 to 4 carbon atoms; or is alkylene of 4 to 18 carbon atoms interrupted by COO and/or phenylene;

T' is tertiary C₄-C₁₈alkyl or phenyl, each of which are unsubstituted or substituted by halogen, OH, COOR₂₁ or C(O)-R₂₂; or T' is C₅-C₁₂cycloalkyl; C₅-C₁₂cycloalkyl which is interrupted by at least one O or -NR₁₈; a polycyclic alkyl radical having 7-18 carbon atoms, or the same

- 4 -

radical which is interrupted by at least one O or -NR₁₈-; or T' is -C(G₁)(G₂)-T''; or C₁-C₁₈alkyl

or C₅-C₁₂cycloalkyl substituted by

$$\begin{array}{c} \text{O} \\ \parallel \\ \text{---P---} \begin{array}{l} \text{OR}_{22} \\ \text{OR}_{22} \end{array} \end{array};$$

T'' is hydrogen, halogen, NO₂, cyano, or is a monovalent organic radical comprising 1-50 carbon atoms;

or T'' and T' together form a divalent organic linking group completing, together with the hindered amine nitrogen atom and the quaternary carbon atom substituted by G₁ and G₂, an optionally substituted five- or six-membered ring structure;

and

R₄ is hydrogen, C₁-C₁₈alkyl, phenyl, an alkali metal cation or a tetraalkylammonium cation;

R₅ and R₆ are hydrogen, C₁-C₁₈alkyl, C₂-C₁₈alkyl which is substituted by hydroxy or, taken together, form a C₂-C₁₂alkylene bridge or a C₂-C₁₂-alkylene bridge interrupted by O or/and NR₁₈;

R₇ is hydrogen, C₁-C₁₈alkyl or C₆-C₁₀aryl;

R₈ is hydrogen, C₁-C₁₈alkyl or C₂-C₁₈hydroxyalkyl;

R₉ is C₁-C₁₂alkylene or a direct bond;


R₁₈ is C₁-C₁₈alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, COOR₂₁ or C(O)-R₂₂;

R₂₁ is hydrogen, a alkali metal atom or C₁-C₁₈alkyl; and

R₂₂ is C₁-C₁₈alkyl;

which process comprises

reacting a N-oxyl amine of formula B




with a compound of formula IV or V



in the presence of an organic hydroperoxide and a catalytic amount of copper or a copper

compound.

Preferred is a process for the synthesis of an amine ether of formula A




wherein

a is 1 or 2;


when a is 1, E is E'

when a is 2, E is L;

E' is C₁-C₃₆ alkyl; C₃-C₁₈ alkenyl; C₂-C₁₈ alkynyl; C₅-C₁₈ cycloalkyl; C₅-C₁₈ cycloalkenyl; a radical of a saturated or unsaturated aliphatic bicyclic or tricyclic hydrocarbon of 7 to 12 carbon atoms; C₂-C₇alkyl or C₃-C₇alkenyl substituted by halogen; C₇-C₁₅ aralkyl or C₇-C₁₅ aralkyl substituted by C₁-C₄ alkyl or phenyl; or E' is a radical of formula (VII)



X is phenyl, naphthyl or biphenyl, which are substituted by 1, 2, 3 or 4 D and optionally further substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino;

D is a group , a group C(O)-G₁₃ or a group C(O)-G₈-C(O)-G₁₃;

G₁ and G₂, independently of each other, are hydrogen, halogen, NO₂, cyano, -CONR₅R₆, -(R₉)COOR₄, -C(O)-R₇, -OR₈, -SR₈, -NHR₈, -N(R₁₈)₂, carbamoyl, di(C₁-C₁₈alkyl)carbamoyl, -C(=NR₅)(NHR₆), C₁-C₁₈alkyl; C₃-C₁₈alkenyl; C₃-C₁₈alkynyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₂-C₁₂heterocycloalkyl; C₁-C₁₈alkyl or C₃-C₁₈alkenyl or C₃-C₁₈alkynyl or C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₂-C₁₂heterocycloalkyl substituted by OH, halogen, NO₂, amino, cyano, carboxy, COOR₂₁, C(O)-R₂₂, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-

C₄alkylamino or di(C₁-C₄alkyl)amino or a group -O-C(O)-R₇; C₂-C₁₈alkyl which is interrupted by at least one O atom and/or NR₅ group; or are C₆-C₁₀aryl; or phenyl or naphthyl which are substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, halogen, cyano, hydroxy, carboxy, COOR₂₁, C(O)-R₂₂, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or G₁ and G₂ together with the linking carbon atom form a C₃-C₁₂cycloalkyl radical;

G₅ and G₆ are independently of each other H or CH₃;


G₉ is C₁-C₁₂alkylene or a direct bond;

G₁₃ is C₁-C₁₈alkyl;

L is alkylene of 1 to 18 carbon atoms, cycloalkylene of 5 to 8 carbon atoms, cycloalkenylene of 5 to 8 carbon atoms, alkenylene of 3 to 18 carbon atoms, alkylene of 1 to 12 carbon atoms substituted by phenyl or by phenyl substituted by alkyl of 1 to 4 carbon atoms;

T' is tertiary C₄-C₁₈alkyl or phenyl, each of which are unsubstituted or substituted by halogen, OH, COOR₂₁ or C(O)-R₂₂; or T' is C₅-C₁₂cycloalkyl; C₅-C₁₂cycloalkyl which is interrupted by at least one O or -NR₁₈; a polycyclic alkyl radical having 7-18 carbon atoms, or the same radical which is interrupted by at least one O or -NR₁₈; or T' is -C(G₁)(G₂)-T''; or C₁-C₁₈alkyl

or C₅-C₁₂cycloalkyl substituted by



T'' is hydrogen, halogen, NO₂, cyano, or is a monovalent organic radical comprising 1-50 carbon atoms;

or T'' and T' together form a divalent organic linking group completing, together with the hindered amine nitrogen atom and the quaternary carbon atom substituted by G₁ and G₂, an optionally substituted five- or six-membered ring structure;

and

R₄ is hydrogen, C₁-C₁₈alkyl, phenyl, an alkali metal cation or a tetraalkylammonium cation;

R₅ and R₆ are hydrogen, C₁-C₁₈alkyl, C₂-C₁₈alkyl which is substituted by hydroxy or, taken together, form a C₂-C₁₂alkylene bridge or a C₂-C₁₂-alkylene bridge interrupted by O or/and NR₁₈;

R₇ is hydrogen, C₁-C₁₈alkyl or C₆-C₁₀aryl;

R₈ is hydrogen, C₁-C₁₈alkyl or C₂-C₁₈hydroxyalkyl;

- 7 -

R_9 is C_1 - C_{12} alkylene or a direct bond;


R_{18} is C_1 - C_{18} alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, $COOR_{21}$ or $C(O)-R_{22}$;

R_{21} is hydrogen, a alkali metal atom or C_1 - C_{18} alkyl; and

R_{22} is C_1 - C_{18} alkyl;

which process comprises

reacting a N-oxyl amine of formula B





with a hydrocarbon of formula IV or V



in the presence of an organic hydroperoxide and a catalytic amount of copper or a copper compound.

In particular, present invention pertains to a process for the synthesis of a hindered amine of formula I or II




- 8 -

wherein


G_1 , G_2 , G_3 and G_4 independently of each other are C_1 - C_{18} alkyl; C_3 - C_{18} alkenyl; C_3 - C_{18} alkinyl; C_1 - C_{18} alkyl or C_3 - C_{18} alkenyl or C_3 - C_{18} alkinyl substituted by OH, halogen or a group $-O-C(O)-R_5$; C_2 - C_{18} alkyl which is interrupted by at least one O atom and/or NR_5 group; or are C_3 - C_{12} cycloalkyl; or C_6 - C_{10} aryl; or G_1 and G_2 and/or G_3 and G_4 together with the linking carbon atom form a C_3 - C_{12} cycloalkyl radical;

a is 1 or 2;

when a is 1, E is E', wherein E' is C_1 - C_{36} alkyl; C_2 - C_{18} alkenyl; C_2 - C_{18} alkynyl; C_5 - C_{18} cycloalkyl; C_5 - C_{18} cycloalkenyl; a radical of a saturated or unsaturated aliphatic bicyclic or tricyclic hydrocarbon of 7 to 12 carbon atoms; C_2 - C_7 alkyl or C_3 - C_7 alkenyl substituted by halogen; C_7 - C_{15} aralkyl or C_7 - C_{15} aralkyl substituted by C_1 - C_4 alkyl or phenyl; or E' is a radical of formula (VII)



X is phenyl, naphthyl or biphenyl, which are substituted by 1, 2, 3 or 4 D and optionally further substituted by NO_2 , halogen, amino, hydroxy, cyano, carboxy, C_1 - C_4 alkoxy, C_1 - C_4 alkylthio, C_1 - C_4 alkylamino or di(C_1 - C_4 alkyl)amino;

D is a group , a group $C(O)-G_{13}$ or a group $C(O)-G_9-C(O)-G_{13}$;

when a is 2, E is L;

G_5 and G_6 are independently of each other H or CH_3 ;

G_9 is C_1 - C_{12} alkylene or a direct bond;


G_{13} is C_1 - C_{18} alkyl;

L is alkylene of 1 to 18 carbon atoms, cycloalkylene of 5 to 8 carbon atoms, cycloalkenylene of 5 to 8 carbon atoms, alkenylene of 3 to 18 carbon atoms, alkylene of 1 to 12 carbon atoms substituted by phenyl or by phenyl substituted by alkyl of 1 to 4 carbon atoms;

T is a divalent organic radical required to complete formula I to form, together with the hindered amine nitrogen atom and the two quaternary carbon atoms substituted by G_1 and G_2 or G_3 and G_4 , a five- or six-membered ring structure;

T_1 is hydrogen, halogen, NO_2 , cyano, $-(\text{R}_9)\text{COOR}_4$, $-(\text{R}_9)\text{C}(\text{O})-\text{R}_7$, $-\text{OR}_8$, unsubstituted C_1 - C_{18} alkyl, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_7 - C_9 phenylalkyl, C_3 - C_{12} cycloalkyl or C_2 - C_{12} heterocycloalkyl; or T_1 is C_1 - C_{18} alkyl, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_7 - C_9 phenylalkyl, C_3 - C_{12} cycloalkyl or C_2 - C_{12} heterocycloalkyl, which is substituted by NO_2 , halogen, hydroxy, cyano, carboxy, C_1 - C_6 alkanoyl, C_1 - C_{12} alkoxy; or phenyl, naphthyl, which are unsubstituted or substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy, C_1 - C_4 alkylthio, halogen, cyano, hydroxy, carboxy; or T_1 is a residue $-\text{CH}_2-\text{O}-\text{R}_{10}$ or $-\text{CH}_2-\text{NR}_{18}-\text{R}_{10}$ or $-\text{C}(=\text{CH}_2)-\text{R}_{11}$ or $-\text{C}(=\text{O})-\text{R}_{12}$;

T_2 is tertiary C_4 - C_{18} alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, COOR_{21} or $\text{C}(\text{O})-\text{R}_{22}$; or T_2 is C_5 - C_{12} cycloalkyl; C_5 - C_{12} cycloalkyl which is interrupted by at least one O; a polycyclic alkyl radical having 7-18 carbon atoms or the same radical which is

interrupted by at least one O atom; or T_2 is $-\text{C}(\text{G}_1)(\text{G}_2)-\text{T}_1$; or 

R_4 is hydrogen, C_1 - C_{18} alkyl, phenyl, an alkali metal cation or a tetraalkylammonium cation;

R_5 is hydrogen, C_1 - C_{18} alkyl or C_6 - C_{10} aryl

R_7 is hydrogen, C_1 - C_{18} alkyl or phenyl;

R_8 is hydrogen, C_1 - C_{18} alkyl or C_2 - C_{18} hydroxyalkyl;

R_9 is C_1 - C_{12} alkylene or a direct bond;

R_{10} is hydrogen, formyl, C_2 - C_{18} alkylcarbonyl, benzoyl, C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl, C_5 - C_{12} cycloalkyl interrupted by O or NR_{18} , or is benzyl or phenyl which are unsubstituted or substituted by halogen, OH, COOR_{21} or $\text{C}(\text{O})-\text{R}_{22}$;

R_{11} is OH, C_1 - C_{18} alkoxy, benzyloxy, $\text{O}-\text{C}(\text{O})-(\text{C}_1-\text{C}_{18})\text{alkyl}$, $\text{N}(\text{R}_{18})_2$, or a group $\text{C}(\text{O})\text{R}_{25}$;

R_{12} is OH, O(alkali-metal), C_1 - C_{18} alkoxy, benzyloxy, $\text{N}(\text{R}_{18})_2$;

R_{18} is C_1 - C_{18} alkyl or C_2 - C_{18} hydroxyalkyl;

R_{21} is hydrogen, an alkali metal atom or C_1 - C_{18} alkyl; and



R_{22} is C_1 - C_{18} alkyl;

R_{25} is OH, C_1 - C_{18} alkoxy, benzyloxy, $\text{N}(\text{R}_{18})_2$;

which process comprises

reacting a N-oxyl hindered amine of formula III or IIIa

- 10 -



with a hydrocarbon of formula IV or V



in the presence of an organic hydroperoxide and a catalytic amount of copper or a copper compound.

In the context of the description of the present invention, the term alkyl comprises, for example, methyl, ethyl and the isomers of propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl and dodecyl. Examples of aryl-substituted alkyl (aralkyl) are benzyl, α -methylbenzyl or cumyl. Examples of alkoxy are methoxy, ethoxy, propoxy, butoxy, octyloxy etc.. Examples of alkenyl are vinyl and especially allyl. Examples of alkylene including alkylidene are ethylene, n-propylene or 1,2-propylene.

Some examples of cycloalkyl are cyclobutyl, cyclopentyl, cyclohexyl, methylcyclopentyl, dimethylcyclopentyl and methylcyclohexyl.

Examples of aryl are phenyl and naphthyl. Examples of substituted aryl are methyl-, dimethyl-, trimethyl-, methoxy- or phenyl-substituted phenyl.

Some examples of an aliphatic carboxylic acid are acetic, propionic, butyric, stearic acid. An example of a cycloaliphatic carboxylic acid is cyclohexanoic acid. An example of an aromatic carboxylic acid is benzoic acid. An example of a phosphorus-containing acid is methylphosphonic acid. An example of an aliphatic dicarboxylic acid is malonyl, maleoyl or


succinyl, or sebacic acid. An example of a residue of an aromatic dicarboxylic acid is phthaloyl.

A group heterocycloalkyl or heterocycloalkenyl embraces one or two heteroatoms, and a group heteroaryl from one to four heteroatoms, the heteroatoms being preferably selected from the group consisting of nitrogen, sulfur and oxygen. Some examples of heterocycloalkyl are tetrahydrofuryl, pyrrolidinyl, piperazinyl and tetrahydrothienyl. Some examples of heteroaryl are furyl, thienyl, pyrrolyl, pyridyl and pyrimidinyl. C₂-C₁₂heterocycloalkyl is typically oxirane, 1,4-dioxane, tetrahydrofuran, γ -butyrolactone, ϵ -caprolactam, oxirane, aziridine, diaziridine, pyrrole, pyrrolidine, thiophen, furan, pyrazole, imidazole, oxazole, oxazolidine, thiazole, pyran, thiopyran, piperidine or morpholine.

An example of a monovalent silyl radical is trimethylsilyl.


Polycyclic alkyl radicals which may also be interrupted by at least one oxygen or nitrogen atom are for example adamantane, cubane, twistane, norbornane, bicyclo[2.2.2]octane

bicyclo[3.2.1]octane, hexamethylenetetramine (urotropine) or a group



Acyl radicals of monocarboxylic acids are, within the definitions, a residue of the formula -CO-R", wherein R" may stand inter alia for an alkyl, alkenyl, cycloalkyl or aryl radical as defined. Preferred acyl radicals include acetyl, benzoyl, acryloyl, methacryloyl, propionyl, butyryl, valeroyl, hexanoyl, heptanoyl, octanoyl, nonanoyl, decanoyl, undecanoyl, dodecanoyl, pentadecanoyl, stearoyl. Polyacyl radicals of polyvalent acids are of the formula (-CO)_n-R", wherein n is the valency, e.g. 2, 3, 4, 5 or 6. Some preferred examples for such residues are given elsewhere.


In preferred products of the instant process, E' is selected from the group consisting of



C₁₂alkyl)₂CCN, -CH₂CH=CH₂, (C₁-C₁₂)alkyl-CR₃₀-C(O)-(C₁-C₁₂)alkyl, (C₁-C₁₂)alkyl-CR₃₀-C(O)-(C₆-C₁₀)aryl, (C₁-C₁₂)alkyl-CR₃₀-C(O)-(C₁-C₁₂)alkoxy, (C₁-C₁₂)alkyl-CR₃₀-C(O)-phenoxy, (C₁-C₁₂)alkyl-CR₃₀-C(O)-N-di(C₁-C₁₂)alkyl, (C₁-C₁₂)alkyl-CR₃₀-CO-NH(C₁-C₁₂)alkyl, (C₁-C₁₂)alkyl-

- 12 -

$\text{CR}_{30}\text{-CO-NH}_2$, $-\text{CH}_2\text{CH=CH-CH}_3$, $-\text{CH}_2\text{-C(CH}_3\text{)=CH}_2$, $-\text{CH}_2\text{-CH=CH-phenyl}$, $-\text{CH}_2\text{-C}\equiv\text{CH}$



R_{30} is hydrogen or $\text{C}_1\text{-C}_{12}$ alkyl;

the aryl groups are phenyl or naphthyl, which are unsubstituted or substituted with $\text{C}_1\text{-C}_{12}$ alkyl, halogen, $\text{C}_1\text{-C}_{12}$ alkoxy, formyl, $\text{C}_2\text{-C}_{12}$ alkylcarbonyl, glycidyloxy, OH, $-\text{COOH}$ or $-\text{COOC}_1\text{-C}_{12}$ alkyl. More preferably E' is selected from the group consisting of $-\text{CH}_2\text{-phenyl}$, $\text{CH}_3\text{CH-phenyl}$, $(\text{CH}_3)_2\text{C-phenyl}$, $(\text{C}_5\text{-C}_6\text{cycloalkyl})_2\text{CCN}$, $(\text{CH}_3)_2\text{CCN}$, $-\text{CH}_2\text{CH=CH}_2$, $\text{CH}_3\text{CH-CH=CH}_2$, $(\text{C}_1\text{-C}_8\text{alkyl})\text{CR}_{30}\text{-C(O)-phenyl}$, $(\text{C}_1\text{-C}_8\text{alkyl})\text{CR}_{30}\text{-C(O)-}(\text{C}_1\text{-C}_8\text{alkoxy})$, $(\text{C}_1\text{-C}_8\text{alkyl})\text{CR}_{30}\text{-C(O)-}(\text{C}_1\text{-C}_8\text{alkyl})$, $(\text{C}_1\text{-C}_8\text{alkyl})\text{CR}_{30}\text{-C(O)-N-di}(\text{C}_1\text{-C}_8\text{alkyl})$, $(\text{C}_1\text{-C}_8\text{alkyl})\text{CR}_{30}\text{-C(O)-NH}(\text{C}_1\text{-C}_8\text{alkyl})$, $(\text{C}_1\text{-C}_8\text{alkyl})\text{CR}_{30}\text{-C(O)-NH}_2$, $(\text{C}_1\text{-C}_{12})\text{alkyl-CR}_{30}\text{-CN}$, wherein R_{30} is hydrogen or $(\text{C}_1\text{-C}_8)$ alkyl.

G_1 and G_2 and/or G_3 and G_4 forming, together with the linking carbon atom, a $\text{C}_3\text{-C}_{12}$ cycloalkyl radical, preferably form a $\text{C}_5\text{-C}_{12}$ cycloalkyl radical, especially cyclopentylene, cyclohexylene or cycloheptylene.

G_1 , G_2 , G_3 and G_4 independently are preferably alkyl of 1 to 4 carbon atoms, or the adjacent radicals G_1 and G_2 and/or G_3 and G_4 together are pentamethylene. More preferably, G_1 , G_2 , G_3 and G_4 independently are methyl or ethyl or propyl, especially methyl or ethyl. In the products most preferred, G_1 and G_3 are each methyl while G_2 and G_4 independently are methyl, ethyl or propyl.

T usually is an organic linking group containing 2-500 carbon atoms and forming, together with the carbon atoms it is directly connected to and the nitrogen atom, a substituted, 5-, 6 or 7-membered cyclic ring structure; T is preferably a $\text{C}_2\text{-C}_{500}$ hydrocarbon optionally containing 1-200 hetero atoms selected from nitrogen, oxygen, phosphorus, sulfur,

silicon and halogen, T therein can be part of a 6-membered cyclic ring structure. More


preferably, T is an organic linking group of the formula
$$\begin{array}{c} \text{H}_2 \\ | \\ \text{E}_1 - \text{C} - \\ | \\ \text{E}_2 \end{array} \quad (\text{VI}), \text{ wherein}$$

E_2 is $-\text{CO}-$ or $-(\text{CH}_2)_b-$, while b is 0, 1 or 2;

E_1 is a carbon atom carrying the two residues R_{24} and R_{25} , or is $>\text{N}-\text{R}_{25}$, or is oxygen, and R_{24} and R_{25} are hydrogen or an organic residue, characterized in that the linking group T in total contains 2-500 carbon atoms and forms, together with the carbon atoms it is directly connected to it and the nitrogen atom, a substituted, 5-, 6 or 7-membered cyclic ring structure, or wherein R_{24} and R_{25} together are $=\text{O}$ or wherein R_{24} is hydrogen and R_{25} is hydrogen or hydroxy. T is most preferably 2-hydroxy-1,3-propanediyl or 2-oxo-1,3-propanediyl.

Preferred products of the formula (I) are those wherein G_1 , G_2 , G_3 and G_4 , independently of each other, are methyl, ethyl, phenyl or COOR_4 ;

E is a carbon centered radical formed from a C_7 - C_{11} phenylalkane or a C_6 - C_{10} pyridylalkane; or C_5 - C_{12} cycloalkane; or C_5 - C_{12} cycloalkene; or an oxacyclohexane or oxycyclohexene; or C_3 - C_8 alkene; or C_3 - C_8 alkene substituted by phenoxy; or a benzene which is substituted by C_1 - C_4 alkyl and a further substituent selected from C_1 - C_4 alkoxy, glycidyl or glycidyl oxy; or E is a radical of formula (VIII)



Ar is C_6 - C_{10} aryl or C_5 - C_9 heteroaryl;

G_{14} is C_1 - C_4 alkyl or an acyl radical of an aliphatic carboxylic acid containing 2 to 4 carbon atoms or benzoyl;


G_{55} is H, CH_3 or phenyl;

G_{66} is $-\text{CN}$ or a group of the formula $-\text{COOR}_4$ or $-\text{CH}_2-\text{O}-\text{G}_{14}$;

R_4 is hydrogen or C_1 - C_8 alkyl;

L is a carbon centered radical formed from propane, butane, pentane, 2,2-dimethyl-propane, xylene; and

- 14 -



T is phenylene or an organic linking group of the formula  (VI), wherein


E_2 is $-\text{CO}-$ or $-(\text{CH}_2)_b-$, while b is 0, 1 or 2;

E_1 is a carbon atom carrying the two residues R_{24} and R_{25} , or is $>\text{N}-R_{25}$, or is oxygen, and R_{24} and R_{25} are hydrogen or an organic residue, characterized in that the linking group T in total contains 2-500 carbon atoms and forms, together with the carbon atoms it is directly connected to it and the nitrogen atom, a substituted, 5-, 6 or 7-membered cyclic ring structure, or wherein R_{24} and R_{25} together are $=\text{O}$ or wherein R_{24} is hydrogen and R_{25} is hydrogen or hydroxy;


or E_1 and E_2 together are 1,2-phenylene.

The product of formula A most preferably corresponds to one of the formulae





(XIII),



(XIV)

wherein

G_1 , G_2 , G_3 and G_4 independently of each other are C_1 - C_{18} alkyl; C_3 - C_{18} alkenyl; C_3 - C_{18} alkinyl; C_1 - C_{18} alkyl or C_3 - C_{18} alkenyl or C_3 - C_{18} alkinyl substituted by OH, halogen or a group $-O-C(O)-$; C_5 - C_{12} cycloalkyl; or phenyl; or G_1 and G_2 and/or G_3 and G_4 together with the linking carbon atom form a C_5 - C_{12} cycloalkyl radical;

Z_1 is O or NR_8 ;

R_8 is hydrogen, OH, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl which are substituted by one or more OH, halogen or a group $-O-C(O)-R_5$, C_2 - C_{18} alkinyl which is interrupted by at least one O atom and/or NR_5 group, C_3 - C_{12} cycloalkyl or C_6 - C_{10} aryl, C_7 - C_9 phenylalkyl, C_5 - C_{10} heteroaryl, $-C(O)-C_1$ - C_{18} alkyl, $-O-C_1$ - C_{18} alkyl or $-COOC_1$ - C_{18} alkyl;

Q is a direct bond or a divalent radical CR_9R_{10} , $CR_9R_{10}-CR_{11}R_{12}$, $CR_9R_{10}CR_{11}R_{12}CR_{13}R_{14}$, $C(O)$ or $CR_9R_{10}C(O)$;

R_9 , R_{10} , R_{11} , R_{12} , R_{13} and R_{14} are independently hydrogen, phenyl, or C_1 - C_{18} alkyl;

T is $CH_2-C(R_{24})(R_{25})-CH_2$, wherein R_{24} and R_{25} together are $=O$ or independently are H, OH or an organic residue, characterized in that the linking group T in total contains 2-500 carbon atoms and optionally 1-200 hetero atoms selected from, oxygen, phosphorus, sulfur, silicon, halogen and tertiary nitrogen. The N-oxyl educts of formulae B, III or IIIa are mostly known in the art; they may be prepared e.g. by the reaction of the corresponding N-H

hindered amine with hydrogen peroxide and sodium tungstate as described by E. G. Rozantsev et al., in *Synthesis*, 1971, 192; or with tert-butyl hydroperoxide and molybdenum (VI) as taught in United States Patent No. 4,691,015, or obtained in analogous manner.

The preferred amount of hydrocarbon for the instant process depends to some extent on the relative number of reactive hydrogens on the hydrocarbon reactant and the hindered amine nitroxyl compound. The reaction is typically carried out with a ratio of 1 to 100 moles of hydrocarbon per mole of nitroxyl moiety with the preferred ratio being 1 to 50 moles per mole of nitroxyl moiety, and the most preferred ratio being 1 to 30 moles of hydrocarbon per mole of nitroxyl moiety.

The preferred amount of organic hydroperoxide is 1 to 20 moles per mole of nitroxyl moiety, with the more preferred amount being 1 to 5 moles of peroxide per mole of nitroxyl moiety and the most preferred amount being 1 to 3 moles of peroxide per mole of nitroxyl moiety.

The organic hydroperoxide used in the process of present invention can be of the formula R-OOH, wherein R usually is a hydrocarbon containing 1-18 carbon atoms. The organic hydroperoxide preferably is a peroxyalcohol containing 3-18 carbon atoms. R is often aliphatic, preferably C₁-C₁₂alkyl. Most preferred organic hydroperoxide is tert.butyl hydroperoxide.

The preferred amount of copper catalyst is from about 0.0001 to 0.5, especially 0.0005 to 0.1 molar equivalent per mole of nitroxyl moiety, with a ratio of 0.001 to 0.05 moles of metal or metal-ligand complex per mole of nitroxyl moiety being the most preferred.

The reaction is preferably run at 0° to 100°C; more preferably at 20° to 100°C, especially in the range 20-80°C.

More specifically, the instant process involves the reaction of a mixture of 1 to 100 moles of the hydrocarbon of formula IV or V, 1 to 20 moles of organic hydroperoxide, and 0.001 mmoles to 0.5 moles of copper catalyst per mole of N-oxyl compound of formula B (1 mmol is 0.001 mol). Preferably, the molar ratio of copper catalyst per mole of N-oxyl compound of formula B is in the range from 1:100 to 1:100000, especially 1:300 to 1:100000.

E is preferably a carbon centered radical formed from a C₇-C₁₁phenylalkane or a C₆-C₁₀pyridylalkane; or C₅-C₁₂cycloalkane; or C₅-C₁₂cycloalkene; or an oxacyclohexane or oxycyclohexene; or C₃-C₈alkene; or C₃-C₈alkene substituted by phenoxy; or a benzene which is substituted by C₁-C₄alkyl and a further substituent selected from C₁-C₄alkoxy, glycidyl or glycidyloxy; or E is a radical of formula (VIII)



Ar is C₆-C₁₀aryl or C₅-C₉heteroaryl;

G₁₄ is C₁-C₄alkyl or an acyl radical of an aliphatic carboxylic acid containing 2 to 4 carbon atoms or benzoyl;

G₅₅ is H, CH₃ or phenyl;

G₆₆ is -CN or a group of the formula -COOR₄ or -CH₂-O-G₁₄;

R₄ is hydrogen or C₁-C₈alkyl;

L is a carbon centered radical formed from propane, butane, pentane, 2,2-dimethyl-propane, xylene.

Important are educts of formula IV or V which are pure hydrocarbons.

The educt of formula IV or V may serve two functions both as reactant and as solvent for the reaction. The reaction can also be carried out using an inert organic or inorganic solvent. A mixture of products may result if the hydrocarbon contains non-equivalent carbon-hydrogen bonds which are reactive in the instant process. For example, cyclohexane can give only one product whereas isopentane can give three distinct reaction products.

Usually the compound of formula IV or V reacts with its most active aliphatic carbon-hydrogen bond.

A solvent may be used, especially if the hydrocarbon of formula IV or V is a solid at the temperature of the reaction or if the catalyst is not very soluble in the hydrocarbon. Inert solvents should have less active carbon-hydrogen bonds; typical inert solvents are acetonitrile, aromatic hydrocarbons like benzene, chlorobenzene, CCl₄, alcohols (e.g. methanol, ethanol, ethylene glycol, ethylene glycol monomethyl ether), or, especially for

reactions with activated hydrocarbons like alkylated aromats or alkenes, also alkanes like hexane, decane etc., or mixtures thereof. Inorganic solvents such as water are possible as well. The reaction can be carried out in one liquid phase or in separate phases.

Good results can be achieved when phase transfer catalysts such as quaternary ammonium or phosphonium salts are used in addition to the copper catalyst. Preferably, quaternary ammonium or phosphonium halogenides such as chlorides or bromides are employed for this purpose. The structure of the ammonium or phosphonium cation is less important; usually, quaternary ammonium or phosphonium cations contain 4 hydrocarbon residues bonded to the central nitrogen or phosphorus atom, which may be, for example, alkyl, phenylalkyl or phenyl groups. Some readily available materials are tetra- C_1 - C_{12} alkylated. The phase transfer catalyst is preferably added in an amount from 0.0001 to 0.5, especially 0.001 to 0.1 molar equivalent per mole of nitroxyl moiety.

The copper catalyst used in the process of the invention is present mainly in the dissolved state. It is often an oxidizable complex ion in the lower oxidation state of a redox system Cu^+/Cu^{2+} or Cu^0/Cu^+ .

The ionic charges are counterbalanced by anionic ligands commonly known in complex chemistry of transition metals, such hydride ions (H^-) or anions derived from inorganic or organic acids, examples being halides, e.g. F^- , Cl^- , Br^- or I^- , fluoro complexes of the type BF_4^- , PF_6^- , SbF_6^- or AsF_6^- , anions of oxygen acids, alcoholates or acetylides or anions of cyclopentadiene.

Anions of oxygen acids are, for example, sulfate, phosphate, perchlorate, perbromate, periodate, antimonate, arsenate, nitrate, carbonate, the anion of a C_1 - C_8 carboxylic acid, such as formate, acetate, propionate, butyrate, benzoate, phenylacetate, mono-, di- or trichloro- or -fluoroacetate, sulfonates, for example methylsulfonate, ethylsulfonate, propylsulfonate, butylsulfonate, trifluoromethylsulfonate (triflate), unsubstituted or C_1 - C_4 alkyl-, C_1 - C_4 alkoxy- or halo-, especially fluoro-, chloro- or bromo-substituted phenylsulfonate or benzylsulfonate, for example tosylate, mesylate, brosylate, p-methoxy- or p-ethoxyphenylsulfonate, pentafluorophenylsulfonate or 2,4,6-triisopropylsulfonate, phosphonates, for example methylphosphonate, ethylphosphonate, propylphosphonate, butylphosphonate, phenylphosphonate, p-methylphenylphosphonate or benzylphosphonate, carboxylates derived from a C_1 - C_8 carboxylic acid, for example formate, acetate, propionate, butyrate, benzoate, phenylacetate, mono-, di- or trichloro- or -fluoroacetate, and also C_1 - C_{12} -alcoholates, such as

straight chain or branched C₁-C₁₂-alcoholates, e.g. methanolate or ethanolate. Also oxides are possible.

Anionic ligands and neutral may also be present up to the preferred coordination number of the complex cation, especially four, five or six. Additional negative charges are counterbalanced by cations, especially monovalent cations such as Na⁺, K⁺, NH₄⁺ or (C₁-C₄ alkyl)₄N⁺.

Suitable neutral ligands are inorganic or organic neutral ligands commonly known in complex chemistry of transition metals. They coordinate to the metal ion through a σ -, π -, μ -, η -type bonding or any combinations thereof up to the preferred coordination number of the complex cation. Suitable inorganic ligands are selected from the group consisting of aquo (H₂O), amino, nitrogen, carbon monoxide and nitrosyl. Suitable organic ligands are selected from the group consisting of phosphines, e.g. (C₆H₅)₃P, (i-C₃H₇)₃P, (C₅H₉)₃P or (C₆H₁₁)₃P, di-, tri-, tetra- and hydroxyamines, such as ethylenediamine, ethylenediaminetetraacetate (EDTA), N,N-Dimethyl-N',N'-bis(2-dimethylaminoethyl)-ethylenediamine (Me₆TREN), catechol, N,N'-dimethyl-1,2-benzenediamine, 2-(methylamino)phenol, 3-(methylamino)-2-butanol or N,N'-bis(1,1-dimethylethyl)-1,2-ethanediamine, N,N,N',N'',N''-pentamethyldiethyltri-amine (PMDETA), C₁-C₆-glycols or glycerides, e.g. ethylene or propylene glycol or derivatives thereof, e.g. di-, tri- or tetraglyme, and monodentate or bidentate heterocyclic e⁻ donor ligands.

Heterocyclic e⁻ donor ligands are derived, for example, from unsubstituted or substituted heteroarenes from the group consisting of furan, thiophene, pyrrole, pyridine, bis-pyridine, picolylimine, g-pyran, g-thiopyran, phenanthroline, pyrimidine, bis-pyrimidine, pyrazine, indole, coumarone, thionaphthene, carbazole, dibenzofuran, dibenzothiophene, pyrazole, imidazole, benzimidazole, oxazole, thiazole, bis-thiazole, isoxazole, isothiazole, quinoline, bis-quinoline, isoquinoline, bis-isoquinoline, acridine, chromene, phenazine, phenoxazine, phenothiazine, triazine, thianthrene, purine, bis-imidazole and bis-oxazole.

The catalyst can be formed in a separate preliminary reaction step from its ligands or is preferably formed in-situ from its transition metal salt, e.g. Cu(I)Cl, which is then converted to the complex compound by addition of compounds corresponding to the ligands present in the complex catalyst, e.g. by addition of ethylenediamine, EDTA, Me₆TREN or PMDETA. These ligand complexes are items of commerce or may be formed in situ by mixing a metal salt with the ligand. The amount of ligand may be less than the amount required to completely complex the metal based on its oxidation state. The metal salt or metal-ligand complex may be bound to a solid support such as silica gel so that it can be recovered and

- 20 -

reused.

Preferred is a process, wherein the active catalyst is a Cu(I) complex ion, especially in the Cu(I)/Cu(II) system.

The instant process can be run in air or in an inert atmosphere such a nitrogen or argon. The instant process can be run under atmospheric pressure as well as under reduced or elevated pressure. Elevated pressure can especially be useful in reactions with a hydrocarbon, which is gaseous under atmospheric pressure and the reaction temperature; in this case, pressure/temperature conditions are advantageous where the hydrocarbon forms a liquid phase or is at least partially dissolved in a suitable solvent.

There are several variations of the instant process. One variation involves the addition of a solution of organic hydroperoxide to a mixture of the N-oxyl hindered amine, the hydrocarbon and cosolvent (if used), and catalyst which has been brought to the desired temperature for reaction. The proper temperature may be maintained by controlling the rate of peroxide addition and/or by using a heating or cooling bath. After the hydroperoxide is added, the reaction mixture is conveniently stirred till the starting N-oxyl compound of formula III has disappeared or is no longer being converted to the compound of formula I and/or II. The reaction can be monitored by methods known in the art such as UV-Vis spectroscopy, thin layer chromatography, gas chromatography or liquid chromatography. Additional portions of catalyst can be added while the reaction is in progress. After the initial hydroperoxide charge has been added to the reaction mixture, more hydroperoxide can be added dropwise to bring the reaction to completion.

A second variation of the instant process is to simultaneously add separate solutions of the hydroperoxide and the nitroxyl compound to a mixture of the hydrocarbon, cosolvent (if used) and catalyst. The nitroxyl compound may be dissolved in water or the alcohol solvent used in the reaction. Some of the nitroxyl compound may be introduced into the reaction mixture prior to starting the peroxide addition, and all of the nitroxyl compound should be added prior to completing the peroxide addition.

Another variation of the instant process involves the simultaneous addition of separate solutions of the hydroperoxide and of the aqueous or alcohol solution of the catalyst to a mixture of the nitroxyl compound, hydrocarbon, and cosolvent (if used). Some

- 21 -


of the metal may be introduced into the reaction mixture prior to starting the peroxide addition.

Still another variation of the instant process is the simultaneous addition of separate solutions of the hydroperoxide, of the aqueous or alcohol solution of the nitroxyl compound, and of an aqueous or alcohol solution of the catalyst to the hydrocarbon and cosolvent (if used). A portion of the nitroxyl compound and/or catalyst may be introduced into the reaction mixture prior to starting the hydroperoxide addition. All of the nitroxyl compound should be added prior to completing the hydroperoxide addition.


If a copper-ligand complex is prepared in situ, the metal salt and ligand are most effectively mixed prior to contact with the nitroxyl compound.

At the end of the reaction, the residual hydroperoxide should be carefully decomposed prior to the isolation of any products.

Examples for compounds which can be obtained advantageously with the process of present invention are those of formulae 1-28:




(1)




(2)


- 22 -




(3)




(4)







(5)




(6)




(7)




- 24 -








(12)








(13)







(14)





- 27 -



wherein in formulas (1) to (15):

- 28 -

m is 0 or 1;

R₁ is hydrogen, hydroxyl or hydroxymethyl;

R₂ is hydrogen, alkyl of 1 to 12 carbon atoms or alkenyl of 2 to 12 carbon atoms;

n is 1 to 4;

when n is 1,

R₃ is alkyl of 1 to 18 carbon atoms, alkoxy-carbonylalkylenecarbonyl of 4 to 18 carbon atoms, alkenyl of 2 to 18 carbon atoms, glycidyl, 2,3-dihydroxypropyl, 2-hydroxy or 2-(hydroxymethyl) substituted alkyl of 3 to 12 carbon atoms which alkyl is interrupted by oxygen, an acyl radical of an aliphatic or unsaturated aliphatic carboxylic or carbamic acid containing 2 to 18 carbon atoms, an acyl radical of a cycloaliphatic carboxylic or carbamic acid containing 7 to 12 carbon atoms, or acyl radical of an aromatic acid containing 7 to 15 carbon atoms;

when n is 2,

R₃ is alkylene of 2 to 18 carbon atoms, a divalent acyl radical of an aliphatic or unsaturated aliphatic dicarboxylic or dicarbamic acid containing 2 to 18 carbon atoms, a divalent acyl radical of a cycloaliphatic dicarboxylic or dicarbamic acid containing 7 to 12 carbon atoms, or a divalent acyl radical of an aromatic dicarboxylic acid containing 8 to 15 carbon atoms;

when n is 3,

R₃ is a trivalent acyl radical of an aliphatic or unsaturated aliphatic tricarboxylic acid containing 6 to 18 carbon atoms, or a trivalent acyl radical of an aromatic tricarboxylic acid containing 9 to 15 carbon atoms;

when n is 4,

R₃ is a tetravalent acyl radical of an aliphatic or unsaturated aliphatic tetracarboxylic acid, especially 1,2,3,4-butanetetracarboxylic acid, 1,2,3,4-but-2-enetetracarboxylic acid, 1,2,3,5-pentanetetracarboxylic acid and 1,2,4,5-pentanetetracarboxylic acid, or R₃ is a tetravalent acyl radical of an aromatic tetracarboxylic acid containing 10 to 18 carbon atoms;

p is 1 to 3,

R₄ is hydrogen, alkyl of 1 to 18 carbon atoms or acyl of 2 to 6 carbon atoms;

- 29 -

when p is 1,

R₅ is hydrogen, alkyl of 1 to 18 carbon atoms, an acyl radical of an aliphatic or unsaturated aliphatic carboxylic or carbamic acid containing 2 to 18 carbon atoms, an acyl radical of a cycloaliphatic carboxylic or carbamic acid containing 7 to 12 carbon atoms, an acyl radical of an aromatic carboxylic acid containing 7 to 15 carbon atoms, or R₄ and R₅ together are -(CH₂)₆CO-, phthaloyl or a divalent acyl radical of maleic acid;

when p is 2,

R₅ is alkylene of 2 to 12 carbon atoms, a divalent acyl radical of an aliphatic or unsaturated aliphatic dicarboxylic or dicarbamic acid containing 2 to 18 carbon atoms, a divalent acyl radical of a cycloaliphatic dicarboxylic or dicarbamic acid containing 7 to 12 carbon atoms, or a divalent acyl radical of an aromatic dicarboxylic acid containing 8 to 15 carbon atoms;

when p is 3,

R₅ is a trivalent acyl radical of an aliphatic or unsaturated aliphatic tricarboxylic acid containing 6 to 18 carbon atoms, or a trivalent acyl radical of an aromatic tricarboxylic acid containing 9 to 15 carbon atoms;

when n is 1,

R₆ is alkoxy of 1 to 18 carbon atoms, alkenyloxy of 2 to 18 carbon atoms, -NHalkyl of 1 to 18 carbon atoms or -N(alkyl)₂ of 2 to 36 carbon atoms,

when n is 2,

R₆ is alkylenedioxy of 2 to 18 carbon atoms, alkenylenedioxy of 2 to 18 carbon atoms, -NH-alkylene-NH- of 2 to 18 carbon atoms or -N(alkyl)-alkylene-N(alkyl)- of 2 to 18 carbon atoms, or R₆ is 4-methyl-1,3-phenylenediamino,

when n is 3,

R₆ is a trivalent alkoxy radical of a saturated or unsaturated aliphatic triol containing 3 to 18 carbon atoms,

when n is 4,


- 30 -

R_6 is a tetravalent alkoxy radical of a saturated or unsaturated aliphatic tetraol containing 4 to 18 carbon atoms,

R_7 and R_8 are independently chlorine, alkoxy of 1 to 18 carbon atoms, $-O-T_1$, amino substituted by 2-hydroxyethyl, $-NH(\text{alkyl})$ of 1 to 18 carbon atoms, $-N(\text{alkyl})T_1$ with alkyl of 1 to 18 carbon atoms, or $-N(\text{alkyl})_2$ of 2 to 36 carbon atoms,

R_9 is oxygen, or R_9 is nitrogen substituted by either hydrogen, alkyl of 1 to 12 carbon atoms or T_1


T_1 is



R_{10} is hydrogen or methyl,

q is 2 to 8,

R_{11} and R_{12} are independently hydrogen or the group T_2



R_{13} is hydrogen, phenyl, straight or branched alkyl of 1 to 12 carbon atoms, alkoxy of 1 to 12 carbon atoms, straight or branched alkyl of 1 to 4 carbon atoms substituted by phenyl, cycloalkyl of 5 to 8 carbon atoms, cycloalkenyl of 5 to 8 carbon atoms, alkenyl of 2 to 12

- 31 -

carbon atoms, glycidyl, allyloxy, straight or branched hydroxyalkyl of 1 to 4 carbon atoms, or silyl or silyloxy substituted three times independently by hydrogen, by phenyl, by alkyl of 1 to 4 carbon atoms or by alkoxy of 1 to 4 carbon atoms;

R_{14} is hydrogen or silyl substituted three times independently by hydrogen, by phenyl, by alkyl of 1 to 4 carbon atoms or by alkoxy of 1 to 4 carbon atoms;

d is 0 or 1;

h is 0 to 4;

k is 0 to 5;

x is 3 to 6;


y is 1 to 10;

z is an integer such that the compound has a molecular weight of 1000 to 4000 amu, e.g. z may be from the range 3-10;

R_{15} is morpholino, piperidino, 1-piperizinyl, alkylamino of 1 to 8 carbon atoms, especially branched alkylamino of 3 to 8 carbon atoms such as tert-octylamino, $-N(alkyl)T_1$ with alkyl of 1 to 8 carbon atoms, or $-N(alkyl)_2$ of 2 to 16 carbon atoms,

R_{16} is hydrogen, acyl of 2 to 4 carbon atoms, carbamoyl substituted by alkyl of 1 to 4 carbon atoms, s-triazinyl substituted once by chlorine and once by R_{15} , or s-triazinyl substituted twice by R_{15} with the condition that the two R_{15} substituents may be different;

R_{17} is chlorine, amino substituted by alkyl of 1 to 8 carbon atoms or by T_1 , $-N(alkyl)T_1$ with alkyl of 1 to 8 carbon atoms, $-N(alkyl)_2$ of 2 to 16 carbon atoms, or the group T_3



R_{18} is hydrogen, acyl of 2 to 4 carbon atoms, carbamoyl substituted by alkyl of 1 to 4 carbon atoms, s-triazinyl substituted twice by $-N(\text{alkyl})_2$ of 2 to 16 carbon atoms or s-triazinyl substituted twice by $-N(\text{alkyl})T_1$ with alkyl of 1 to 8 carbon atoms;

in formulas (16) to (28), R_1 , R_2 , R_7 , R_8 , R_9 , R_{10} , R_{13} , R_{14} , d, h, k, m, q, and T_1 have the same meanings as in formulas (1) to (15);

R_{19} is hydrogen, alkyl of 1 to 18 carbon atoms, alkenyl of 2 to 18 carbon atoms, glycidyl, 2,3-dihydroxypropyl, 2-hydroxy or 2-(hydroxymethyl) substituted alkyl of 3 to 12 carbon atoms which alkyl is interrupted by oxygen, an acyl radical of an aliphatic or unsaturated aliphatic carboxylic or carbamic acid containing 2 to 18 carbon atoms, an acyl radical of a cycloaliphatic carboxylic or carbamic acid containing 7 to 12 carbon atoms, or acyl radical of an aromatic acid containing 7 to 15 carbon atoms;

R_{20} is alkylene of 2 to 18 carbon atoms, a divalent acyl radical of an aliphatic or unsaturated aliphatic dicarboxylic or dicarbamic acid containing 2 to 18 carbon atoms, a divalent acyl radical of a cycloaliphatic dicarboxylic or dicarbamic acid containing 7 to 12 carbon atoms, or a divalent acyl radical of an aromatic dicarboxylic acid containing 8 to 15 carbon atoms;

R_{21} is hydrogen, alkyl of 1 to 18 carbon atoms or acyl of 2 to 6 carbon atoms;

R_{22} is hydrogen, alkyl of 1 to 18 carbon atoms, an acyl radical of an aliphatic or unsaturated aliphatic carboxylic or carbamic acid containing 2 to 18 carbon atoms, an acyl radical of a cycloaliphatic carboxylic or carbamic acid containing 7 to 12 carbon atoms, an acyl radical of an aromatic carboxylic acid containing 7 to 15 carbon atoms, or R_4 and R_5 together are $-(CH_2)_5CO-$, phthaloyl or a divalent acyl radical of maleic acid;

R₂₃ is hydrogen, alkyl of 1 to 4 carbon atoms or acyl of 2 to 6 carbon atoms;

R₂₄ is alkylene of 2 to 18 carbon atoms, a divalent acyl radical of an aliphatic or unsaturated aliphatic dicarboxylic or dicarbamic acid containing 2 to 18 carbon atoms, a divalent acyl radical of a cycloaliphatic dicarboxylic or dicarbamic acid containing 7 to 12 carbon atoms, or a divalent acyl radical of an aromatic dicarboxylic acid containing 8 to 15 carbon atoms;

R₂₅ is alkoxy of 1 to 18 carbon atoms, alkenyloxy of 2 to 18 carbon atoms, -NHalkyl of 1 to 18 carbon atoms or -N(alkyl)₂ of 2 to 36 carbon atoms,

R₂₆ is alkylenedioxy of 2 to 18 carbon atoms, alkenylenedioxy of 2 to 18 carbon atoms, -NH-alkylene-NH- of 2 to 18 carbon atoms or -N(alkyl)-alkylene-N(alkyl)- of 3 to 18 carbon atoms.



E is a carbon centered radical formed preferably from a C₇-C₁₁phenylalkane, especially toluene, ethylbenzene, isopropylbenzene; or C₅-C₁₂cycloalkane, especially cyclohexene; or C₅-C₁₂cycloalkene, especially cyclohexene; or C₃-C₈alkene, especially propene; or a benzene which is substituted by C₁-C₄alkyl and a further substituent selected from C₁-C₄alkoxy, glycidyl or glycidyloxy.

L is a carbon centered radical formed preferably from propane, butane, pentane, 2,2-dimethyl-propane, xylene, diethylbenzene.

Preferably, the reaction site in the compound E-H or H-L-H is an activated carbon-hydrogen bond, whose carbon, for example, is linked to an electron pushing functional group or a functional group able to stabilize the radical formed after cleavage of the carbon-hydrogen bond. Electron withdrawing groups, if present in E-H or H-L-H, are preferably not directly linked to the reactive site.

Some compounds obtainable by the instant process are novel compounds. Thus, another object of the invention is a compound of the formula XV or XVI

- 34 -





wherein

G_1 and G_2 independently are methyl or ethyl;

G_3 is C_2 - C_8 alkenyl; C_2 - C_8 alkenyl substituted by phenyl, C_1 - C_4 alkyl-phenyl, cyclohexyl, C_1 - C_4 alkyl-cyclohexyl or $COX'G_8$; or G_3 is OG_{10} ; or is a carbon-bonded 5- or 6-membered unsubstituted or alkyl substituted heterocyclic residue containing 3-12 carbon atoms, especially 5 carbon atoms in total and whose heteroatoms are selected from nitrogen and oxygen;

G_4 is as defined for G_3 or is C_1 - C_{18} alkyl, provided that G_4 is not methyl when G_3 is C_2 -alkenyl; or G_3 and G_4 together with the carbon atom they are attached to form the residue $Ph-CH-CN$, or form a carbon-bonded 5- or especially 6-membered unsubstituted or possibly alkyl substituted, unsaturated heterocyclic residue containing 3-12 carbon atoms in total, especially 5 carbon atoms in total, whose heteroatoms are selected from nitrogen and oxygen;

G_6 is H; OH; OR_3 ; NR_4R_5 ; $(CO)R_6$; or is a radical of formula





G_7 is H;

or G_6 and G_7 together are $=O$ or a residue of formula $-O-CH_2-C(R_1)(R_2)-(CH_2)_m-O-$;

G_8 is hydrogen or C_1 - C_8 alkyl or C_2 - C_8 hydroxyalkyl, especially C_1 - C_8 alkyl;
 G'_8 is hydrogen or C_1 - C_8 alkyl or C_2 - C_8 hydroxyalkyl or C_2 - C_8 alkenyl; G_{10} is C_1 - C_{18} alkyl; C_1 - C_{18} alkyl substituted by phenyl or C_1 - C_{12} alkyl, C_1 - C_{12} alkoxy and/or OH substituted phenyl; phenyl; phenyl substituted by C_1 - C_{12} alkyl, C_1 - C_{12} alkoxy, OH; or is a carbon-bonded 5- or 6-membered unsubstituted or alkyl substituted heterocyclic residue containing 3-12 carbon atoms and whose heteroatoms are selected from nitrogen and oxygen;
 G_{15} is H or methyl;

G_{16} is OH; OR_3 ; NR_4R_5 ; $(CO)R_6$; or is a radical of formula



G_{17} is H;

or G_{18} and G_{17} together are $=O$ or a residue of formula $-O-CH_2-C(R_1)(R_2)-(CH_2)_m-O-$;

G_{18} is H or methyl or $=O$;

Ph is phenyl or phenyl substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy, halogen and/or nitro;

m is 0 or 1;

R_1 is hydrogen, C_1 - C_4 alkyl, hydroxyl or hydroxymethyl;

R_2 is hydrogen, alkyl of 1 to 12 carbon atoms or alkenyl of 2 to 12 carbon atoms;

R_3 is alkyl of 1 to 18 carbon atoms, alkoxy carbonylalkylenecarbonyl of 4 to 18 carbon atoms, alkenyl of 2 to 18 carbon atoms, glycidyl, 2,3-dihydroxypropyl, 2-hydroxy or 2-(hydroxymethyl) substituted alkyl of 3 to 12 carbon atoms which alkyl is interrupted by oxygen, an acyl radical of an aliphatic or unsaturated aliphatic carboxylic or carbamic acid containing 2 to 18 carbon atoms, an acyl radical of a cycloaliphatic carboxylic or carbamic acid containing 7 to 12 carbon atoms, or acyl radical of an aromatic acid containing 7 to 15 carbon atoms;

R_4 is hydrogen, alkyl of 1 to 18 carbon atoms or acyl of 2 to 6 carbon atoms;

- 36 -

R_5 is hydrogen, alkyl of 1 to 18 carbon atoms, an acyl radical of an aliphatic or unsaturated aliphatic carboxylic or carbamic acid containing 2 to 18 carbon atoms, an acyl radical of a cycloaliphatic carboxylic or carbamic acid containing 7 to 12 carbon atoms, an acyl radical of an aromatic carboxylic acid containing 7 to 15 carbon atoms, or R_4 and R_5 together are - $(CH_2)_5CO-$, phthaloyl or a divalent acyl radical of maleic acid;

R_6 is alkoxy of 1 to 18 carbon atoms, alkenyloxy of 2 to 18 carbon atoms, -NHalkyl of 1 to 18 carbon atoms or -N(alkyl)₂ of 2 to 36 carbon atoms;

R_7 and R_8 are independently chlorine, alkoxy of 1 to 18 carbon atoms, amino substituted by 2-hydroxyethyl, -NH(alkyl) of 1 to 18 carbon atoms, or -N(alkyl)₂ of 2 to 36 carbon atoms;

R_9 is oxygen, or R_9 is nitrogen substituted by hydrogen or alkyl of 1 to 12 carbon atoms;


R_{13} is silyl or silyloxy substituted three times independently by hydrogen, by phenyl, by alkyl of 1 to 4 carbon atoms or by alkoxy of 1 to 4 carbon atoms;

R_{30} is H, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl, C₃-C₁₆alkoxyalkyl;


X' is O or NG_8 ;

Y-Z is $>C(G_{17})G_{16}$ or O or $>N-R_{30}$.

Another object of the invention is compound of the formula XVII or XVIII



(XVII)



(XVIII)

- 37 -

wherein

G_1 , G_2 and G_3 are independently methyl or ethyl;


G_{20} is H, C_1 - C_{18} alkyl or C_5 - C_{12} cycloalkyl, especially C_1 - C_{12} alkyl;

G_{21} and G_{22} are independently hydrogen, halogen, C_1 - C_{12} alkyl or C_1 - C_{12} alkoxy;

G_{23} is oxyl, OH or OE, where E is as defined in claim 1;

G_{24} is methyl, ethyl or phenyl.

Preferred is a compound of the formula XV



wherein



G_1 and G_2 independently are methyl or ethyl;

G_3 is C_2 - C_8 alkenyl; C_2 - C_8 alkenyl substituted by phenyl, C_1 - C_4 alkyl-phenyl, cyclohexyl, C_1 - C_4 alkyl-cyclohexyl or $COX'G_8$; OG_{10} ; or is a carbon-bonded 5- or 6-membered unsubstituted or alkyl substituted heterocyclic residue containing 3-12 carbon atoms and whose heteroatoms are selected from nitrogen and oxygen;

G_4 is as defined for G_3 or is C_1 - C_{18} alkyl;

or G_3 and G_4 together with the carbon atom they are attached to form a carbon-bonded 5- or 6-membered unsubstituted or alkyl substituted heterocyclic residue containing 3-12 carbon atoms, whose heteroatoms are selected from nitrogen and oxygen;

G_5 is hydrogen;



G₇ is H;

or G₆ and G₇ together are =O or a residue of formula -O-CH₂-C(R₁)(R₂)-(CH₂)_m-O-;

G₈ is hydrogen or C₁-C₈alkyl or C₂-C₈hydroxyalkyl;

G₁₀ is C₁-C₁₈alkyl; C₁-C₁₈alkyl substituted by phenyl or C₁-C₁₂alkyl, C₁-C₁₂alkoxy and/or OH substituted phenyl; phenyl; phenyl substituted by C₁-C₁₂alkyl, C₁-C₁₂alkoxy, OH; or is a carbon-bonded 5- or 6-membered unsubstituted or alkyl substituted heterocyclic residue containing 3-12 carbon atoms and whose heteroatoms are selected from nitrogen and oxygen;

m is 0 or 1;

R₁ is hydrogen, hydroxyl or hydroxymethyl;

R₂ is hydrogen, alkyl of 1 to 12 carbon atoms or alkenyl of 2 to 12 carbon atoms;

R₃ is alkyl of 1 to 18 carbon atoms, alkoxycarbonylalkylenecarbonyl of 4 to 18 carbon atoms, alkenyl of 2 to 18 carbon atoms, glycidyl, 2,3-dihydroxypropyl, 2-hydroxy or 2-(hydroxymethyl) substituted alkyl of 3 to 12 carbon atoms which alkyl is interrupted by oxygen, an acyl radical of an aliphatic or unsaturated aliphatic carboxylic or carbamic acid containing 2 to 18 carbon atoms, an acyl radical of a cycloaliphatic carboxylic or carbamic acid containing 7 to 12 carbon atoms, or acyl radical of an aromatic acid containing 7 to 15 carbon atoms;

R₄ is hydrogen, alkyl of 1 to 18 carbon atoms or acyl of 2 to 6 carbon atoms;

R₅ is hydrogen, alkyl of 1 to 18 carbon atoms, an acyl radical of an aliphatic or unsaturated aliphatic carboxylic or carbamic acid containing 2 to 18 carbon atoms, an acyl radical of a cycloaliphatic carboxylic or carbamic acid containing 7 to 12 carbon atoms, an acyl radical of an aromatic carboxylic acid containing 7 to 15 carbon atoms, or R₄ and R₅ together are - (CH₂)₅CO-, phthaloyl or a divalent acyl radical of maleic acid;

R₆ is alkoxy of 1 to 18 carbon atoms, alkenyloxy of 2 to 18 carbon atoms, -NHalkyl of 1 to 18 carbon atoms or -N(alkyl)₂ of 2 to 36 carbon atoms;

R₇ and R₈ are independently chlorine, alkoxy of 1 to 18 carbon atoms, amino substituted by 2-hydroxyethyl, -NH(alkyl) of 1 to 18 carbon atoms, or -N(alkyl)₂ of 2 to 36 carbon atoms;

R₉ is oxygen, or R₉ is nitrogen substituted by hydrogen or alkyl of 1 to 12 carbon atoms;

R₁₃ is silyl or silyloxy substituted three times independently by hydrogen, by phenyl, by alkyl of 1 to 4 carbon atoms or by alkoxy of 1 to 4 carbon atoms;

X' is O or NH.

Preferred compounds are those wherein the carbon-bonded 5- or 6-membered unsubstituted or alkyl substituted heterocyclic residue containing 3-12 carbon atoms, whose heteroatoms are selected from nitrogen and oxygen, is pyridyl; furyl; di- or tetrahydrofuryl; pyryl; di- or tetrahydropyryl; dioxanyl; or one of these residues substituted by C₁-C₄alkyl. Further preferences are as described above for formula A.

Compounds of the formula A and XV can be employed with advantage for stabilizing organic material against the damaging effect of light, oxygen and/or heat, especially for stabilizing synthetic organic polymers or compositions containing them. They are notable for high thermal stability, substrate compatibility and good persistence in the substrate. Examples of polymers which can be stabilized in this way are the following:

1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybut-1-ene, poly-4-methylpent-1-ene, polyisoprene or polybutadiene, as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high density polyethylene (HDPE), high density and high molecular weight polyethylene (HDPE-HMW), high density and ultrahigh molecular weight polyethylene (HDPE-UHMW), medium density polyethylene (MDPE), low density polyethylene (LDPE), linear low density polyethylene (LLDPE), (VLDPE) and (ULDPE).

Polyolefins, i.e. the polymers of monoolefins exemplified in the preceding paragraph, preferably polyethylene and polypropylene, can be prepared by different, and especially by the following, methods:

- a) radical polymerisation (normally under high pressure and at elevated temperature).
- b) catalytic polymerisation using a catalyst that normally contains one or more than one metal of groups IVb, Vb, VIb or VIII of the Periodic Table. These metals usually have one or more than one ligand, typically oxides, halides, alcoholates, esters, ethers, amines, alkyls, alkenyls and/or aryls that may be either π - or σ -coordinated. These metal complexes may be in the free form or fixed on substrates, typically on activated magnesium chloride, titanium(III) chloride, alumina or silicon oxide. These catalysts may be soluble or insoluble in the polymerisation medium. The catalysts can be used by themselves in the polymerisation or further activators may be used,

typically metal alkyls, metal hydrides, metal alkyl halides, metal alkyl oxides or metal alkyloxanes, said metals being elements of groups Ia, IIa and/or IIIa of the Periodic Table. The activators may be modified conveniently with further ester, ether, amine or silyl ether groups. These catalyst systems are usually termed Phillips, Standard Oil Indiana, Ziegler (-Natta), TNZ (DuPont), metallocene or single site catalysts (SSC).

2. Mixtures of the polymers mentioned under 1), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).
3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, for example ethylene/propylene copolymers, linear low density polyethylene (LLDPE) and mixtures thereof with low density polyethylene (LDPE), propylene/but-1-ene copolymers, propylene/isobutylene copolymers, ethylene/but-1-ene copolymers, ethylene/hexene copolymers, ethylene/methylpentene copolymers, ethylene/heptene copolymers, ethylene/octene copolymers, propylene/butadiene copolymers, isobutylene/isoprene copolymers, ethylene/alkyl acrylate copolymers, ethylene/alkyl methacrylate copolymers, ethylene/vinyl acetate copolymers and their copolymers with carbon monoxide or ethylene/acrylic acid copolymers and their salts (ionomers) as well as terpolymers of ethylene with propylene and a diene such as hexadiene, dicyclopentadiene or ethylidene-norbornene; and mixtures of such copolymers with one another and with polymers mentioned in 1) above, for example polypropylene/ethylene-propylene copolymers, LDPE/ethylene-vinyl acetate copolymers (EVA), LDPE/ethylene-acrylic acid copolymers (EAA), LLDPE/EVA, LLDPE/EAA and alternating or random polyalkylene/carbon monoxide copolymers and mixtures thereof with other polymers, for example polyamides.
4. Hydrocarbon resins (for example C₅-C₉) including hydrogenated modifications thereof (e.g. tackifiers) and mixtures of polyalkylenes and starch.
5. Polystyrene, poly(p-methylstyrene), poly(α -methylstyrene).
6. Copolymers of styrene or α -methylstyrene with dienes or acrylic derivatives, for example styrene/butadiene, styrene/acrylonitrile, styrene/alkyl methacrylate, styrene/butadiene/alkyl

acrylate, styrene/butadiene/alkyl methacrylate, styrene/maleic anhydride, styrene/acrylonitrile/methyl acrylate; mixtures of high impact strength of styrene copolymers and another polymer, for example a polyacrylate, a diene polymer or an ethylene/propylene/diene terpolymer; and block copolymers of styrene such as styrene/butadiene/styrene, styrene/isoprene/styrene, styrene/ethylene/butylene/styrene or styrene/ethylene/propylene/styrene.

7. Graft copolymers of styrene or α -methylstyrene, for example styrene on polybutadiene, styrene on polybutadiene-styrene or polybutadiene-acrylonitrile copolymers; styrene and acrylonitrile (or methacrylonitrile) on polybutadiene; styrene, acrylonitrile and methyl methacrylate on polybutadiene; styrene and maleic anhydride on polybutadiene; styrene, acrylonitrile and maleic anhydride or maleimide on polybutadiene; styrene and maleimide on polybutadiene; styrene and alkyl acrylates or methacrylates on polybutadiene; styrene and acrylonitrile on ethylene/propylene/diene terpolymers; styrene and acrylonitrile on polyalkyl acrylates or polyalkyl methacrylates, styrene and acrylonitrile on acrylate/butadiene copolymers, as well as mixtures thereof with the copolymers listed under 6), for example the copolymer mixtures known as ABS, MBS, ASA or AES polymers.

8. Halogen-containing polymers such as polychloroprene, chlorinated rubbers, chlorinated and brominated copolymer of isobutylene-isoprene (halobutyl rubber), chlorinated or sulfochlorinated polyethylene, copolymers of ethylene and chlorinated ethylene, epichlorohydrin homo- and copolymers, especially polymers of halogen-containing vinyl compounds, for example polyvinyl chloride, polyvinylidene chloride, polyvinyl fluoride, polyvinylidene fluoride, as well as copolymers thereof such as vinyl chloride/vinylidene chloride, vinyl chloride/vinyl acetate or vinylidene chloride/vinyl acetate copolymers.

9. Polymers derived from α,β -unsaturated acids and derivatives thereof such as polyacrylates and polymethacrylates; polymethyl methacrylates, polyacrylamides and polyacrylonitriles, impact-modified with butyl acrylate.

10. Copolymers of the monomers mentioned under 9) with each other or with other unsaturated monomers, for example acrylonitrile/butadiene copolymers, acrylonitrile/alkyl acrylate copolymers, acrylonitrile/alkoxyalkyl acrylate or acrylonitrile/vinyl halide copolymers or acrylonitrile/alkyl methacrylate/butadiene terpolymers.

- 42 -

11. Polymers derived from unsaturated alcohols and amines or the acyl derivatives or acetals thereof, for example polyvinyl alcohol, polyvinyl acetate, polyvinyl stearate, polyvinyl benzoate, polyvinyl maleate, polyvinyl butyral, polyallyl phthalate or polyallyl melamine; as well as their copolymers with olefins mentioned in 1) above.

12. Homopolymers and copolymers of cyclic ethers such as polyalkylene glycols, polyethylene oxide, polypropylene oxide or copolymers thereof with bisglycidyl ethers.

13. Polyacetals such as polyoxymethylene and those polyoxymethylenes which contain ethylene oxide as a comonomer; polyacetals modified with thermoplastic polyurethanes, acrylates or MBS.

14. Polyphenylene oxides and sulfides, and mixtures of polyphenylene oxides with styrene polymers or polyamides.

15. Polyurethanes derived from hydroxyl-terminated polyethers, polyesters or polybutadienes on the one hand and aliphatic or aromatic polyisocyanates on the other, as well as precursors thereof.

16. Polyamides and copolyamides derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, for example polyamide 4, polyamide 6, polyamide 6/6, 6/10, 6/9, 6/12, 4/6, 12/12, polyamide 11, polyamide 12, aromatic polyamides starting from m-xylene diamine and adipic acid; polyamides prepared from hexamethylenediamine and isophthalic or/and terephthalic acid and with or without an elastomer as modifier, for example poly-2,4,4-trimethylhexamethylene terephthalamide or poly-m-phenylene isophthalamide; and also block copolymers of the aforementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, e.g. with polyethylene glycol, polypropylene glycol or polytetramethylene glycol; as well as polyamides or copolyamides modified with EPDM or ABS; and polyamides condensed during processing (RIM polyamide systems).

17. Polyureas, polyimides, polyamide-imides, polyetherimids, polyesterimids, polyhydantoins and polybenzimidazoles.

18. Polyesters derived from dicarboxylic acids and diols and/or from hydroxycarboxylic acids or the corresponding lactones, for example polyethylene terephthalate, polybutylene terephthalate, poly-1,4-dimethylolcyclohexane terephthalate and polyhydroxybenzoates, as well as block copolyether esters derived from hydroxyl-terminated polyethers; and also polyesters modified with polycarbonates or MBS.
19. Polycarbonates and polyester carbonates.
20. Polysulfones, polyether sulfones and polyether ketones.
21. Crosslinked polymers derived from aldehydes on the one hand and phenols, ureas and melamines on the other hand, such as phenol/formaldehyde resins, urea/formaldehyde resins and melamine/formaldehyde resins.
22. Drying and non-drying alkyd resins.
23. Unsaturated polyester resins derived from copolyesters of saturated and unsaturated dicarboxylic acids with polyhydric alcohols and vinyl compounds as crosslinking agents, and also halogen-containing modifications thereof of low flammability.
24. Crosslinkable acrylic resins derived from substituted acrylates, for example epoxy acrylates, urethane acrylates or polyester acrylates.
25. Alkyd resins, polyester resins and acrylate resins crosslinked with melamine resins, urea resins, isocyanates, isocyanurates, polyisocyanates or epoxy resins.
26. Crosslinked epoxy resins derived from aliphatic, cycloaliphatic, heterocyclic or aromatic glycidyl compounds, e.g. products of diglycidyl ethers of bisphenol A and bisphenol F, which are crosslinked with customary hardeners such as anhydrides or amines, with or without accelerators.
27. Blends of the aforementioned polymers (polyblends), for example PP/EPDM, Polyamide/EPDM or ABS, PVC/EVA, PVC/ABS, PVC/MBS, PC/ABS, PBTP/ABS, PC/ASA, PC/PBT, PVC/CPE, PVC/acrylates, POM/thermoplastic PUR, PC/thermoplastic PUR,

POM/acrylate, POM/MBS, PPO/HIPS, PPO/PA 6.6 and copolymers, PA/HDPE, PA/PP, PA/PPO, PBT/PC/ABS or PBT/PET/PC.

Of particular interest is the use of compounds of the formula XV as stabilizers in synthetic organic polymers, for example a coating or a bulk polymer or article formed therefrom, especially in thermoplastic polymers and corresponding compositions as well as in coating compositions. Thermoplastic polymers of most importance in present compositions are polyolefines and their copolymers, such as listed above under items 1-3, thermoplastic polyolefin (TPO), thermoplastic polyurethan (TPU), thermoplastic rubber (TPR), polycarbonate, such as in item 19 above, and blends, such as in item 28 above. Of utmost importance are polyethylene (PE), polypropylene (PP), polycarbonate (PC) and polycarbonate blends such as PC/ABS blends, as well as in acid or metal catalyzed coating compositions.

In general the compounds of present invention are added to the material to be stabilized in amounts of from 0.1 to 10 %, preferably from 0.01 to 5 %, in particular from 0.01 to 2 % (based on the material to be stabilized). Particular preference is given to the use of the novel compounds in amounts of from 0.05 to 1.5 %, especially from 0.1 to 0.5 %. Where compounds of present invention are used as flame retardants, dosages are usually higher, e.g. 0.1 to 25 % by weight, mainly 0.1 to 10 % by weight of the organic material to be stabilized and protected against inflammation.

Used in polymerizable compositions as a polymerization regulator or initiator, preferably the regulator/initiator compound is present in an amount of from 0.01 mol-% to 30 mol-%, more preferably in an amount of from 0.1 mol-% to 20 mol-% and most preferred in an amount of from 0.5 mol-% to 10 mol-% based on the monomer or monomer mixture.

Incorporation into the materials can be effected, for example, by mixing in or applying the compounds of the formula A or XV and, if desired, further additives by the methods which are customary in the art. Where polymers are involved, especially synthetic polymers, incorporation can take place prior to or during the shaping operation, or by applying the dissolved or dispersed compound to the polymer, with or without subsequent evaporation of the solvent. In the case of elastomers, these can also be stabilized as latices. A further possibility for incorporating the compounds of the formula XV into polymers is to add them before, during or directly after the polymerization of the corresponding monomers or prior to

crosslinking. In this context the compound of the formula XV can be added as it is or else in encapsulated form (for example in waxes, oils or polymers). In the case of addition prior to or during the polymerization, the compounds of the formula XV can also act as a regulator of the chain length of the polymers (chain terminator).

The compounds of the formula XV can also be added in the form of a masterbatch containing said compound in a concentration, for example, of from 2.5 to 25 % by weight to the polymers that are to be stabilized.

The compounds of the formula XV can judiciously be incorporated by the following methods:

- as emulsion or dispersion (e.g. to latices or emulsion polymers),
- as a dry mixture during the mixing in of additional components or polymer mixtures,
- by direct introduction into the processing apparatus (e.g. extruders, internal mixers, etc),
- as solution or melt.

Novel polymer compositions can be employed in various forms and/or processed to give various products, for example as (to give) films, fibres, tapes, moulding compositions, profiles, or as binders for coating materials, adhesives or putties.

In addition to the compounds of the formula XV the novel compositions may as additional component C comprise one or more conventional additives such as, for example, those indicated below.

1. Antioxidants

1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol, nonylphenols which are linear or branched in the side chains, for example, 2,6-di-nonyl-4-methylphenol, 2,4-dimethyl-6-(1'-methylundec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methylheptadec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methyltridec-1'-yl)phenol and mixtures thereof.

1.2. Alkylthiomethylphenols, for example 2,4-dioctylthiomethyl-6-tert-butylphenol, 2,4-dioctylthiomethyl-6-methylphenol, 2,4-dioctylthiomethyl-6-ethylphenol, 2,6-di-dodecylthiomethyl-4-nonylphenol.

1.3. Hydroquinones and alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-diphenyl-4-octadecyloxyphenol, 2,6-di-tert-butylhydroquinone, 2,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyphenyl stearate, bis-(3,5-di-tert-butyl-4-hydroxyphenyl) adipate.

1.4. Tocopherols, for example α -tocopherol, β -tocopherol, γ -tocopherol, δ -tocopherol and mixtures thereof (Vitamin E).

1.5. Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-methylphenol), 4,4'-thiobis-(3,6-di-sec-amylphenol), 4,4'-bis(2,6-dimethyl-4-hydroxyphenyl)disulfide.

1.6. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-(α,α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl]terephthalate, 1,1-bis-(3,5-dimethyl-2-hydroxyphenyl)butane, 2,2-bis-(3,5-di-tert-butyl-4-hydroxyphenyl)propane, 2,2-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylmercaptobutane, 1,1,5,5-tetra-(5-tert-butyl-4-hydroxy-2-methylphenyl)pentane.

1.7. O-, N- and S-benzyl compounds, for example 3,5,3',5'-tetra-tert-butyl-4,4'-dihydroxydibenzyl ether, octadecyl-4-hydroxy-3,5-dimethylbenzylmercaptoacetate, tridecyl-4-hydroxy-3,5-di-tert-butylbenzylmercaptoacetate, tris(3,5-di-tert-butyl-4-hydroxybenzyl)amine, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithioterephthalate, bis(3,5-di-tert-butyl-4-hydroxybenzyl)sulfide, isooctyl-3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate.

1.8. Hydroxybenzylated malonates, for example dioctadecyl-2,2-bis-(3,5-di-tert-butyl-2-hydroxybenzyl)-malonate, di-octadecyl-2-(3-tert-butyl-4-hydroxy-5-methylbenzyl)-malonate, didodecylmercaptoethyl-2,2-bis-(3,5-di-tert-butyl-4-hydroxybenzyl)malonate, bis[4-(1,1,3,3-tetramethylbutyl)phenyl]-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate.

1.9. Aromatic hydroxybenzyl compounds, for example 1,3,5-tris-(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, 1,4-bis(3,5-di-tert-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)phenol.

1.10. Triazine Compounds, for example 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,3,5-triazine, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,2,3-triazine, 1,3,5-tris-(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)isocyanurate, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenylethyl)-1,3,5-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hexahydro-1,3,5-triazine, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate.

1.11. Benzylphosphonates, for example dimethyl-2,5-di-tert-butyl-4-hydroxybenzylphosphonate, diethyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-5-tert-butyl-4-hydroxy-3-methylbenzylphosphonate, the calcium salt of the monoethyl ester of 3,5-di-tert-butyl-4-hydroxybenzylphosphonic acid.

1.12. Acylaminophenols, for example 4-hydroxylauranilide, 4-hydroxystearanilide, octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.

1.13. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.14. Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.15. Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.16. Esters of 3,5-di-tert-butyl-4-hydroxyphenyl acetic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.17. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid e.g. N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamide, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamide, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazide, N,N'-bis[2-(3-[3,5-di-tert-butyl-4-hydroxyphenyl]propionyloxy)ethyl]oxamide (Naugard®XL-1 supplied by Uniroyal).

1.18. Ascorbic acid (vitamin C)

1.19. Aminic antioxidants, for example N,N'-di-isopropyl-p-phenylenediamine, N,N'-di-sec-butyl-p-phenylenediamine, N,N'-bis(1,4-dimethylpentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methylpentyl)-p-phenylenediamine, N,N'-bis(1-methylheptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylenediamine, N,N'-diphenyl-p-phenylenediamine, N,N'-bis(2-naphthyl)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-phenylenediamine, N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluenesulfamoyl)diphenylamine, N,N'-dimethylhexyl-N'-phenyl-p-phenylenediamine, N-allyldiphenylamine, 4-isopropoxy-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-phenyl-1-naphthylamine, N-(4-tert-octylphenyl)-1-naphthylamine, N-phenyl-2-naphthylamine, octylated diphenylamine, for example p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-butyrylaminophenol, 4-nonanoylaminophenol, 4-dodecanoylaminophenol, 4-octadecanoylaminophenol, bis(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylaminomethylphenol, 2,4'-diaminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetramethyl-4,4'-diaminodiphenylmethane, 1,2-bis[(2-methylphenyl)amino]ethane, 1,2-bis(phenylamino)propane, (o-tolyl)biguanide, bis[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, a mixture of mono- and dialkylated tert-butyl/tert-octyldiphenylamines, a mixture of mono- and dialkylated nonyldiphenylamines, a mixture of mono- and dialkylated dodecyldiphenylamines, a mixture of mono- and dialkylated isopropyl/isohexyldiphenylamines, a mixture of mono- and dialkylated tert-butyl/diphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, a mixture of mono- and dialkylated tert-butyl/tert-octylphenothiazines, a mixture of mono- and dialkylated tert-octylphenothiazines, N-allylphenothiazin, N,N,N',N'-tetraphenyl-1,4-diaminobut-2-ene, N,N-bis(2,2,6,6-tetramethyl-piperid-4-yl)-hexamethylenediamine, bis(2,2,6,6-tetramethylpiperid-4-yl)-sebacate, 2,2,6,6-tetramethylpiperidin-4-one, 2,2,6,6-tetramethylpiperidin-4-ol.

2. UV absorbers and light stabilisers

2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example 2-(2'-hydroxy-5'-methylphenyl)-benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chloro-benzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-

hydroxy-4'-octyloxyphenyl)benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxyphenyl)benzotriazole, 2-(3',5'-bis-(α,α -dimethylbenzyl)-2'-hydroxyphenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)-carbonylethyl]-2'-hydroxyphenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonylethyl]-2'-hydroxyphenyl)benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxycarbonylethyl)phenyl)benzotriazole, 2,2'-methylene-bis-[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazole-2-ylphenol]; the transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonylethyl)-2'-hydroxyphenyl]-2H-benzotriazole with polyethylene glycol 300; $\left[R - CH_2CH_2 - COO - CH_2CH_2 \right]_2$ where R = 3'-tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-ylphenyl, 2-[2'-hydroxy-3'-(α,α -dimethylbenzyl)-5'-(1,1,3,3-tetramethylbutyl)phenyl]benzotriazole; 2-[2'-hydroxy-3'-(1,1,3,3-tetramethylbutyl)-5'-(α,α -dimethylbenzyl)phenyl]benzotriazole.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octyloxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of substituted and unsubstituted benzoic acids, as for example 4-tertbutyl-phenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoyl resorcinol, bis(4-tert-butylbenzoyl) resorcinol, benzoyl resorcinol, 2,4-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate, hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, 2-methyl-4,6-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate.

2.4. Acrylates, for example ethyl α -cyano- β,β -diphenylacrylate, isooctyl α -cyano- β,β -diphenylacrylate, methyl α -carbomethoxycinnamate, methyl α -cyano- β -methyl-p-methoxy-cinnamate, butyl α -cyano- β -methyl-p-methoxy-cinnamate, methyl α -carbomethoxy-p-methoxycinnamate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.

2.5. Nickel compounds, for example nickel complexes of 2,2'-thio-bis-[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyldithiocarbamate,

nickel salts of the monoalkyl esters, e.g. the methyl or ethyl ester, of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphenyl undecylketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or without additional ligands.

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(2,2,6,6-tetramethyl-4-piperidyl)succinate, bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(1,2,2,6,6-pentamethyl-4-piperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensate of 1-(2-hydroxyethyl)-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, linear or cyclic condensates of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl)nitritotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butane-tetracarboxylate, 1,1'-(1,2-ethanediyl)-bis(3,3,5,5-tetramethylpiperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearyl-2,2,6,6-tetramethylpiperidine, bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-3,5-di-tert-butylbenzyl)malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decan-2,4-dione, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)succinate, linear or cyclic condensates of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, the condensate of 2-chloro-4,6-bis(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, the condensate of 2-chloro-4,6-di-(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidin-2,5-dione, 3-dodecyl-1-(1,2,2,6,6-pentamethyl-4-piperidyl)pyrrolidin-2,5-dione, a mixture of 4-hexadecyloxy- and 4-stearyl-2,2,6,6-tetramethylpiperidine, a condensation product of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-cyclohexylamino-2,6-dichloro-1,3,5-triazine, a condensation product of 1,2-bis(3-aminopropylamino)ethane and 2,4,6-trichloro-1,3,5-triazine as well as 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [136504-96-6]); N-(2,2,6,6-tetramethyl-4-piperidyl)-n-dodecylsuccinimid, N-(1,2,2,6,6-pentamethyl-4-piperidyl)-n-dodecylsuccinimid, 2-undecyl-7,7,9,9-tetramethyl-1-oxa-3,8-diaza-4-oxo-spiro[4,5]decane, a reaction product of 7,7,9,9-tetramethyl-2-cycloundecyl-1-oxa-3,8-diaza-4-oxospiro [4,5]decane und epichlorohydrin, 1,1-bis(1,2,2,6,6-pentamethyl-4-piperidyl)oxycarbonyl-2-(4-methoxyphenyl)ethene, N,N'-bis-formyl-N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine, diester of 4-methoxy-

methylene-malonic acid with 1,2,2,6,6-pentamethyl-4-hydroxypiperidine, poly[methylpropyl-3-oxy-4-(2,2,6,6-tetramethyl-4-piperidyl)]siloxane, reaction product of maleic acid anhydride- α -olefin-copolymer with 2,2,6,6-tetramethyl-4-aminopiperidine or 1,2,2,6,6-pentamethyl-4-aminopiperidine, 2,4-bis[N-(1-cyclohexyloxy-2,2,6,6-tetramethylpiperidine-4-yl)-N-butyl-amino]-6-(2-hydroxyethyl)amino-1,3,5-triazine.

2.7. Oxamides, for example 4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butoxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butoxanilide, 2-ethoxy-2'-ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxamide, 2-ethoxy-5-tert-butyl-2'-ethoxanilide and its mixture with 2-ethoxy-2'-ethyl-5,4'-di-tert-butoxanilide, mixtures of o- and p-methoxy-disubstituted oxanilides and mixtures of o- and p-ethoxy-disubstituted oxanilides.

2.8. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-tridecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-butyloxy-propoxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxy-propyloxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[4-(dodecyloxy/tridecyloxy-2-hydroxypropoxy)-2-hydroxy-phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-dodecyloxy-propoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-hexyloxy)phenyl-4,6-diphenyl-1,3,5-triazine, 2-(2-hydroxy-4-methoxyphenyl)-4,6-diphenyl-1,3,5-triazine, 2,4,6-tris[2-hydroxy-4-(3-butoxy-2-hydroxy-propoxy)phenyl]-1,3,5-triazine, 2-(2-hydroxyphenyl)-4-(4-methoxyphenyl)-6-phenyl-1,3,5-triazine, 2-[2-hydroxy-4-[3-(2-ethylhexyl-1-oxy)-2-hydroxypropyloxy]phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-[1-octyloxycarbonyl-ethoxy]phenyl]-4,6-bis(4-phenylphenyl)-1,3,5-triazine wherein the octyl moiety is a mixture of different isomers.


3. Metal deactivators, for example N,N'-diphenyloxamide, N-salicylal-N'-salicyloyl hydrazine, N,N'-bis(salicyloyl) hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl) hydrazine, 3-salicyloylamino-1,2,4-triazole, bis(benzylidene)oxalyl dihydrazide, oxanilide, isophthaloyl





dihydrazide, sebacoyl bisphenylhydrazide, N,N'-diacetyl adipoyl dihydrazide, N,N'-bis(salicyloyl)oxalyl dihydrazide, N,N'-bis(salicyloyl)thiopropionyl dihydrazide.

4. Phosphites and phosphonites, for example triphenyl phosphite, diphenyl alkyl phosphites, phenyl dialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythritol diphosphite, bis(2,6-di-tert-butyl-4-methylphenyl)-pentaerythritol diphosphite, diisodecyl oxypentaerythritol diphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)pentaerythritol diphosphite, bis(2,4,6-tris(tert-butylphenyl)pentaerythritol diphosphite, tristearyl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylene diphosphonite, 6-isooctyloxy-2,4,8,10-tetra-tert-butyl-12H-dibenz[d,g]-1,3,2-dioxaphosphocin, 6-fluoro-2,4,8,10-tetra-tert-butyl-12-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, bis(2,4-di-tert-butyl-6-methylphenyl) methyl phosphite, bis(2,4-di-tert-butyl-6-methylphenyl) ethyl phosphite, 2,2',2''-nitrido[triethyltris(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl)phosphite], 2-ethylhexyl(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl)phosphite.

Especially preferred are the following phosphites:

Tris(2,4-di-tert-butylphenyl) phosphite (Irgafos®168, Ciba-Geigy), tris(nonylphenyl) phosphite,





5. Hydroxylamines, for example, N,N-dibenzylhydroxylamine, N,N-diethylhydroxylamine, N,N-dioctylhydroxylamine, N,N-dilaurylhydroxylamine, N,N-ditetradecylhydroxylamine, N,N-dihexadecylhydroxylamine, N,N-dioctadecylhydroxylamine, N-hexadecyl-N-octadecylhydroxylamine, N-heptadecyl-N-octadecylhydroxylamine, N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

6. Nitrones, for example, N-benzyl-alpha-phenyl-nitrone, N-ethyl-alpha-methyl-nitrone, N-octyl-alpha-heptyl-nitrone, N-lauryl-alpha-undecyl-nitrone, N-tetradecyl-alpha-tridcyl-nitrone, N-

hexadecyl-alpha-pentadecyl-nitrone, N-octadecyl-alpha-heptadecyl-nitrone, N-hexadecyl-alpha-heptadecyl-nitrone, N-octadecyl-alpha-pentadecyl-nitrone, N-heptadecyl-alpha-heptadecyl-nitrone, N-octadecyl-alpha-hexadecyl-nitrone, nitrone derived from N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

7. Thiosynergists, for example, dilauryl thiodipropionate or distearyl thiodipropionate.

8. Peroxide scavengers, for example esters of β -thiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters, mercaptobenzimidazole or the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide, pentaerythritol tetrakis(β -dodecylmercapto)propionate.

9. Polyamide stabilisers, for example, copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

10. Basic co-stabilisers, for example, melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids for example calcium stearate, zinc stearate, magnesium behenate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate or zinc pyrocatecholate.

11. Nucleating agents, for example, inorganic substances such as talcum, metal oxides such as titanium dioxide or magnesium oxide, phosphates, carbonates or sulfates of, preferably, alkaline earth metals; organic compounds such as mono- or polycarboxylic acids and the salts thereof, e.g. 4-tert-butylbenzoic acid, adipic acid, diphenylacetic acid, sodium succinate or sodium benzoate; polymeric compounds such as ionic copolymers (ionomers).

12. Fillers and reinforcing agents, for example, calcium carbonate, silicates, glass fibres, glass bulbs, asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black, graphite, wood flour and flours or fibers of other natural products, synthetic fibers.

13. Other additives, for example, plasticisers, lubricants, emulsifiers, pigments, rheology additives, catalysts, flow-control agents, optical brighteners, flameproofing agents, antistatic agents and blowing agents.

14. Benzofuranones and indolinones, for example those disclosed in U.S. 4,325,863; U.S. 4,338,244; U.S. 5,175,312; U.S. 5,216,052; U.S. 5,252,643; DE-A-4316611; DE-A-4316622; DE-A-4316876; EP-A-0589839 or EP-A-0591102 or 3-[4-(2-acetoxyethoxy)phenyl]-5,7-di-tert-butyl-benzofuran-2-one, 5,7-di-tert-butyl-3-[4-(2-stearoyloxyethoxy)phenyl]benzofuran-2-one, 3,3'-bis[5,7-di-tert-butyl-3-(4-[2-hydroxyethoxy]phenyl)benzofuran-2-one], 5,7-di-tert-butyl-3-(4-ethoxyphenyl)benzofuran-2-one, 3-(4-acetoxy-3,5-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,5-dimethyl-4-pivaloyloxyphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,4-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(2,3-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one.

The conventional additives are judiciously employed in amounts of 0.1-10 % by weight, for example 0.2-5 % by weight, based on the material to be stabilized.


The following examples are for illustrative purposes only and are not to be construed to limit the instant invention in any manner whatsoever. Percentages given are usually percent by weight if not otherwise indicated. Abbreviations used:

min. minutes;


HPLC high pressure liquid chromatography;

GC gas chromatography.


Example 1: Preparation of




A mixture of 0.85 ml 1-oxyl-2,2,6,6-tetramethyl-4-propoxypiperidine, 4.67 ml of a 53.4 % solution of tert.butyl hydroperoxide in decane, and 25 mg CuCl_2 (as a 1% solution in ethanol; ratio catalyst:nitroxyl = 1:2000 {mol/mol}) and 4.95 g ethylbenzene is stirred at 60°C. After 60 min., the reaction is terminated by pouring the mixture into 30 ml of a solution of 10% Na_2SO_3 in water. The flask is washed twice with 20 ml ethyl acetate in total, which is added to the water/reaction mixture. The organic layer is separated and washed twice with 40 ml water in total. Distillation of solvent yields 1.46 g (97% of theory) of the above product (purity 95%, GC).

Example 2: Preparation of

A mixture of 0.85 ml 1-oxyl-2,2,6,6-tetramethyl-4-propoxypiperidine, 4.67 ml of a 53.4 % solution of tert.butyl hydroperoxide in decane, 25 mg CuCl₂ (as a 1% solution in ethanol) and 3.83 g cyclohexene is stirred at 60°C. After 12 min., the reaction is terminated and the product recovered as described in example 1. Distillation of solvent yields 1.05 g (95% of theory) of the above product (purity more than 98%, GC).

Example 3: Preparation of

A mixture of 0.85 ml 1-oxyl-2,2,6,6-tetramethyl-4-propoxypiperidine, 4.67 ml of a 53.4 % solution of tert.butyl hydroperoxide in decane, 100 mg CuCl₂ (as a 1% solution in ethanol) and 3.92 g cyclohexane is stirred at 60°C. After 200 min., the reaction is terminated and the product recovered as described in example 1. Distillation of solvent yields 0.90 g (81% of theory) of the above product.

Examples 4-8: Preparation of


To a mixture of 0.53 ml 1-oxyl-2,2,6,6-tetramethyl-4-propoxypiperidine (= 1 equivalent), 2.92 ml of a 53.4 % solution of tert.butyl hydroperoxide in decane (6 equivalents), and 3.96 ml (10 equivalents) of 4-glycidyloxy-1-ethylbenzene, 10⁻³ equivalents of the catalyst indicated in the following table are added as a 1% b.w. solution in ethanol. Examples 7 and 8 are carried out using iron instead of copper catalysts for comparison purposes. The mixture is stirred at

60°C for the reaction time indicated. Subsequently, the reaction is terminated by pouring the mixture into 30 ml of a solution of 10% Na_2SO_3 in water. The flask is washed twice with 20 ml of ethyl acetate in total, which is added to the water/reaction mixture. The organic layer is separated and washed twice with 40 ml of water in total. The above product is isolated by distillation; catalysts, reaction time and yields are given in the following table 1.


Tab. 1: Yield and reaction times using copper or iron catalysts

<u>Example</u>	<u>Catalyst</u>	<u>Reaction Time</u>	<u>Yield</u>
4	CuCl	20 min.	85 %
5	CuCl	20 min.	85 %
6	CuCl_2	20 min.	83 %
7 (comparison)	FeCl_2	180 min.	5 %
8 (comparison)	FeBr_3	180 min.	6 %


The enormous advantage achievable by the use of a copper catalyst is evident.



A mixture of 0.85 ml 1-oxyl-2,2,6,6-tetramethyl-4-propoxypiperidine, 4.67 ml of a 53.4 % solution of tert.butyl hydroperoxide in decane, 25 mg CuCl_2 (as a 1% solution in ethanol; giving a ration catalyst:educt = 1:2000) and 5.00 g 4-ethylpyridine is stirred at 60°C for 2.5 h. The reaction mixture is poured into 30 ml of a solution of 10% by weight of Na_2SO_3 in water, the flask washed twice with 10 ml of ethyl acetate, respectively, and these washings are added to the aqueous reaction mixture. Separating the organic layer, washing twice with water (2 x 20 ml) and distillation yields 1.46 g (97% of theory) of the above product, purity 95% (GC).

Example 10:

Reaction is performed as described in Example 9, with 6.26 g of allyl-phenyl-ether instead of 4-ethylpyridine. This yields 1.56 g (96%) of the above product, purity >98% (GC).


Example 11:

Reaction is performed as described in Example 9, with 3.91 g of 3,4-dihydro-2H-pyran instead of 4-ethylpyridine and termination of reaction after 8 minutes. This yields 1.12 g (100%) of the above product.

Example 12: Preparation of 1-(1-phenylethyl)oxy-2,2,6,6-tetramethylpiperidine

A mixture of 0.5 g (3.2 mmol; 1 eq.) 1-oxy-2,2,6,6-tetramethylpiperidine (TEMPO), 1.24 g of a 70 % aq. solution of tert.butyl hydroperoxide (9.6 mmol; 3 eq.), CuBr₂ catalyst as described in the table below and 3.4 g (32 mmol, 10 eq.) of ethylbenzene is stirred at 60°C for 1 h. In some of the preparations, 0.032 mmol (0.01 eq. relative to TEMPO) of a phase transfer catalyst as shown in the table is added. Reaction and work-up is done as described in example 1. Yield is determined by means of quantitative HPLC.

- 60 -



Run	CuBr ₂	Phase Transfer Catalyst	Yield
1	0.357 mg	none	35 %
2	0.357 mg	10.3 mg tetrabutylammonium bromide	73 %
3	0.357 mg	14.4 mg trioctyl-methyl ammonium bromide	78 %
4	7.15 mg	none	

Amounts of copper catalyst 0.375 mg are 0.0016 mmol (0.0005 eq.); 7.15 mg are 0.032 mmol (0.01 eq. rel. to TEMPO).

This example shows that the reaction speed may be increased by adding a phase transfer catalyst or by greatly increasing the amount of copper catalyst.

Example 13: 2,6-Diethyl-2,3,6-trimethyl-1-(1-phenyl-ethoxy)-piperidine (101)

2.4 ml of a solution of 13.4 g of CuCl₂ and 4.24 g of LiCl in 153 ml of ethanol are added to a solution of 29.75 g (0.15 mol) of 2,6-diethyl-2,3,6-trimethyl-piperidine-1-oxyl (accessible according to US 4 131 599) in 92 ml (0.75 mol) of ethylbenzene. 28.7 g (0.22 mol) of *t*-butyl hydroperoxide (70% in water) are then added dropwise to the stirred mixture at 65°C under argon. The mixture is then stirred at 65-70°C until the red nitroxide colour disappears (approximately 3 to 4 hours). After cooling to 20°C, a solution of 12 g of Na₂S₂O₅ in 60 ml of water is added. After stirring for a further 60 minutes, the organic phase is separated off, washed with 2x50 ml of 20% Na₂CO₃ and 2x50 ml of water, dried over MgSO₄ and concentrated by evaporation using a rotary evaporator to yield 41.5 g (91%) of the title compound in the form of a colourless oil.

¹H-NMR (300 MHz, CDCl₃): 7.3-7.2 m (5H), 4.75-4.68 m (1H), 2.13-0.53 m (27H).

Example 14: 1,3,3-Trimethyl-2-(1-phenyl-ethoxy)-1,2,3,4-tetrahydro-isoquinoline-1-carboxylic acid methyl ester

a) 1,3,3-Trimethyl-1,2,3,4-tetrahydro-isoquinoline-1-carboxylic acid methyl ester-2-oxyl 111 ml (0.67 mol) of a 40% peracetic acid in acetic acid are added dropwise over a period of 30 minutes at 10-20°C to a solution of 78 g (0.334 mol) of 1,3,3-trimethyl-1,2,3,4-tetrahydro-isoquinoline-1-carboxylic acid methyl ester (see *Synthesis* 677 (1997) for preparation) in 300 ml of ethyl acetate. The mixture is stirred for a further 13 hours at 20°C and then diluted with 650 ml of water. The organic phase is separated off, washed with 2x250 ml of water and then with 2x250 ml of 10% NaHCO₃ solution, dried over MgSO₄ and concentrated by evaporation using a rotary evaporator. Chromatography of the residue using hexane/ethyl acetate (2:1) on 1600 g of silica gel and subsequent recrystallisation from hexane yields 44.6 g (54%) of 1,3,3-trimethyl-1,2,3,4-tetrahydro-isoquinoline-1-carboxylic acid methyl ester-2-oxyl in the form of orange crystals, m.p. 53-56°C.

For C₁₄H₁₈NO₃ calculated C 67.72%, H 7.31%, N 5.64%; found C 67.46%, H 7.28%, N 5.64%.

b) Analogously to Example 13, 3.14 g (89%) of compound of example (a) are prepared from 2.5 g (0.01 mol) of 1,3,3-trimethyl-1,2,3,4-tetrahydro-isoquinoline-1-carboxylic acid methyl ester-2-oxyl, 20 ml (0.163 mol) of ethylbenzene, 2.25 g (0.017 mol) of *t*-butyl hydroperoxide (70% in water) and 0.2 ml of the copper(II) chloride solution described in Example 13. Colourless resin is obtained after chromatography on silica gel using hexane/ethyl acetate (6:1). ¹H-NMR (300 MHz, CDCl₃), mixture of 2 diastereoisomers: 7.33-6.80 m (9H), 4.96-4.69 m (1H), 3.72-0.88 m (17H).

Example 15: 1-Methyl-1,3,3-triphenyl-2-(1-phenyl-ethoxy)-2,3-dihydro-1.H.-isoindole

a) 1-Methyl-1,3,3-triphenyl-2,3-dihydro-1.H.-isoindole

17.3 g (0.05 mol) of 1,1,3-triphenyl-1.H.-isoindole (see *Zh. Org. Khim.* 2449 (1975) for preparation) are slowly added under argon to a stirred solution of 21.9 g (1 mol) of methyl-lithium in 115 ml of tetrahydrofuran. The mixture is then heated at 70°C for 5 hours and subsequently stirred at 20°C for 12 hours. 100 ml of toluene and 80 ml of saturated NH₄Cl solution are then added, and the organic phase is separated off, washed with water and concentrated by evaporation using a rotary evaporator. Chromatography of the residue using hexane/ethyl acetate (49:1) on 250 g of silica gel and subsequent recrystallisation from acetonitrile/methanol yields 10.6 g (58%) of 1-methyl-1,3,3-triphenyl-2,3-dihydro-1.H.-isoindole in the form of colourless crystals, m.p. 106-108°C.

For $C_{27}H_{23}N$ calculated C 89.71%, H 6.41%, N 3.87%; found C 89.67%, H 6.51%, N 3.80%.

b) 1-Methyl-1,3,3-triphenyl-2,3-dihydro-1.H.-isoindole-2-oxyl

12.3 g (0.05 mol) of m-chloroperbenzoic acid (70%) are added to a solution of 9.05 g (0.025 mol) of 1-methyl-1,3,3-triphenyl-2,3-dihydro-1.H.-isoindole in 60 ml of tetrahydrofuran. The mixture is stirred at room temperature for 3 hours, then diluted with 50 ml of hexane and 50 ml of ethyl acetate, washed three times with 100 ml of 10% $NaHCO_3$ solution and concentrated by evaporation using a rotary evaporator. Chromatography of the residue using toluene on 150 g of silica gel and subsequent recrystallisation from hexane yields 7.7 g (82%) of 1-methyl-1,3,3-triphenyl-2,3-dihydro-1.H.-isoindole-2-oxyl in the form of orange crystals, m.p. 119-124°C.

For $C_{27}H_{22}NO$ calculated C 86.14%, H 5.89%, N 3.72%; found C 86.18%, H 5.89%, N 3.68%.

c) Analogously to Example 13, 2.2 g (76%) of the title compound are prepared in the form of colourless crystals (pentane), m.p. 124-141°C, from 2.26 g (0.006 mol) of 1-methyl-1,3,3-triphenyl-2,3-dihydro-1.H.-isoindole-2-oxyl, 20 ml (0.163 mol) of ethylbenzene, 2.53 g (0.02 mol) of *t*-butyl hydroperoxide (70% in water), 0.2 g of tetrabutylammonium bromide and 0.25 ml of the copper(II) chloride solution described in Example 13.

1H -NMR (300 MHz, $CDCl_3$), mixture of 2 diastereoisomers: 7.95-6.66 m (ArH), 4.64-4.51 m (1H), 1.58 s (Me), 1.43 s (Me), 1.12 d, $J = 9$ Hz, (Me), 0.86 d, $J = 9$ Hz, (Me).

Example 16: 1,1,3,3-Tetraphenyl-2-(1-phenyl-ethoxy)-2,3-dihydro-1.H.-isoindole

a) 1,1,3,3-Tetraphenyl-2,3-dihydro-1.H.-isoindole-2-oxyl

22 g (0.089 mol) of m-chloroperbenzoic acid (70%) are added to a solution of 9.5 g (0.022 mol) of 1,1,3,3-tetraphenyl-2,3-dihydro-1.H.-isoindole (see *J. Org. Chem.* 461 (1969) for preparation) in 85 ml of tetrahydrofuran. The mixture is stirred at room temperature for 46 hours, then diluted with 50 ml of toluene and 50 ml of ethyl acetate, washed twice with 100 ml of 10% $NaHCO_3$ solution and concentrated by evaporation using a rotary evaporator. The residue is dissolved again in 100 ml of tetrahydrofuran and is oxidised with a further 10 g (0.04 mol) of m-chloroperbenzoic acid over a period of 20 hours. After the addition of 100 ml of toluene, the residue is washed twice with 100 ml of 10% $NaHCO_3$, dried over $MgSO_4$ and concentrated by evaporation. Crystallisation of the residue from toluene/-dichloromethane yields 12.55 g of 1,1,3,3-tetraphenyl-2,3-dihydro-1.H.-isoindole-2-oxyl in the form of orange crystals, m.p. 250-253°C.

For $C_{32}H_{24}NO$ calculated C 87.64%, H 5.52%, N 3.19%; found C 87.46%, H 5.58%, N 3.37%.

b) Analogously to Example 13, 2.39 g (88%) of the title compound 104 are prepared in the form of colourless crystals (hexane), m.p. 166-171°C, from 2.2 g (0.005 mol) of 1,1,3,3-tetraphenyl-2,3-dihydro-1H-indole-2-oxyl, 20 ml (0.163 mol) of ethylbenzene, 2.1 g (0.016 mol) of *t*-butyl hydroperoxide (70% in water), 0.2 g of tetrabutylammonium bromide and 0.2 ml of the copper(II) chloride solution described in Example 13.

1H -NMR (300 MHz, $CDCl_3$): 7.75-6.56 m (29H), 4.75-4.68 q, $J = 9$ Hz, (1H), 1.58 s (Me), 0.97 d, $J = 9$ Hz, (Me).

Example 17: Phenyl-(2,2,6,6-tetramethyl-piperidin-1-yloxy)-acetic acid methyl ester

4.2 ml (0.03 mol) of *t*-butyl hydroperoxide (70% in water) and 0.4 ml of the copper(II) chloride solution described in Example 13 are added to a solution of 3.15 g (0.02 mol) of 2,2,6,6-tetramethyl-piperidine-1-oxyl in 14 ml (0.1 mol) of phenylacetic acid methyl ester. The mixture is then stirred at 60°C under argon until the red colour of the nitroxide disappears (approximately 5 hours). After cooling to room temperature, a solution of 3 g of $Na_2S_2O_5$ in 25 ml of water is added and the mixture was stirred vigorously for a further 10 minutes. The organic phase is then separated off and the excess phenylacetic acid methyl ester is distilled off at 0.1 mbar. The residue is chromatographed on 100 g of silica gel using hexane/ethyl acetate (20:1) and then recrystallised from hexane to yield 3.65 g (59%) of the title compound in the form of colourless crystals, m.p. 83-86°C.

1H -NMR (300 MHz, $CDCl_3$): 7.45-7.26 m (5H), 5.21 s (1H), 3.65 s (Me), 1.64-1.28 m (6H), 1.23 s (Me), 1.14 s (Me), 1.07 s (Me), 0.72 s (Me).

Example 18: 2,2-Dimethyl-propionic acid 1-(methoxycarbonyl-phenyl-methoxy)-2,2,6,6-tetramethyl-piperidin-4-yl ester

Analogously to Example 17, 4.42 g (54%) of the title compound are obtained in the form of colourless crystals, m.p. 138-141°C, from 5.13 g (0.02 mol) of 2,2-dimethyl-propionic acid 2,2,6,6-tetramethyl-piperidin-4-yl ester-1-oxyl (prepared from pivaloyl chloride and 2,2,6,6-tetramethyl-4-hydroxy-piperidine-1-oxyl in pyridine, m.p. 94-97°C), 14 ml (0.1 mol) of phenylacetic acid methyl ester, 4.2 ml (0.03 mol) of *t*-butyl hydroperoxide (70% in water) and 0.4 ml of the copper(II) chloride solution described in Example 13.

¹H-NMR (300 MHz, CDCl₃): 7.44-7.26 m (5H), 5.19 s (1H), 5.03-4.93 m (1H), 3.66 s (Me), 1.87-1.43 m (4H), 1.34 s (Me), 1.19 s (Me), 1.17 s (Me), 1.16 s (t-Bu), 0.76 s (Me).

Example 19: (4-Acetylamino-2,2,6,6-tetramethyl-piperidin-1-yloxy)-phenyl-acetic acid methyl ester

Analogously to Example 17, 21.5 g (59%) of the title compound are obtained in the form of colourless crystals, m.p. 160-161°C, from 21.23 g (0.1 mol) of 4-acetylamino-2,2,6,6-tetramethyl-piperidine-1-oxyl, 70.4 ml (0.5 mol) of phenylacetic acid methyl ester, 20.6 ml (0.15 mol) of *t*-butyl hydroperoxide (70% in water) and 2 ml of the copper(II) chloride solution described in Example 13.

¹H-NMR (300 MHz, CDCl₃): 7.44-7.26 m (5H), 5.18 s (1H), 5.11 s (1H), 4.15-4.13 m (1H), 3.66 s (Me), 1.93 s (Me), 1.85-1.26 m (4H), 1.58 s (Me), 1.35 s (Me), 1.18 s (Me), 0.75 s (Me).

Example 20: (4-tert-Butyl-2,2-diethyl-6,6-dimethyl-3-oxo-piperazin-1-yloxy)-phenylacetic acid methyl ester

Analogously to Example 17, 4.9 g (60%) of the title compound are obtained in the form of colourless crystals, m.p. 85-90°C, from 5.1 g (0.02 mol) of 4-tert-butyl-2,2-diethyl-6,6-dimethyl-3-oxo-piperazine-1-oxyl (see Ger. Offen. DE 199 49 352 A1 for preparation), 14 ml (0.1 mol) of phenylacetic acid methyl ester, 4.2 ml (0.03 mol) of *t*-butyl hydroperoxide (70% in water) and 0.4 ml of the copper(II) chloride solution described in Example 13.

¹H-NMR (300 MHz, CDCl₃): 7.42-7.26 m (5H), 5.19-5.18 bs (1H), 3.68 s (Me), 3.11-2.95 m (2H), 1.39 s (t-Bu), 2.25-0.73 m (16 H).

Example 21: (4-tert-Butyl-2,2-diethyl-6,6-dimethyl-3-oxo-piperazin-1-yloxy)-phenylacetic acid

2 g (0.0049 mol) of compound of example 20 are added to a solution of 2 g of KOH in 15 ml of methanol and the mixture is stirred at room temperature for 15 hours. It is then concentrated by evaporation using a rotary evaporator and the residue is dissolved in 15 ml of water and acidified with 4 ml of HCl (32%). The resulting precipitate is filtered off with suction and recrystallised from acetonitrile to yield 1.2 g (62%) of the title compound in the form of colourless crystals, m.p. 125-133°C.

¹H-NMR (300 MHz, CDCl₃): 7.41-7.26 m (5H), 5.19 s (1H), 3.07-2.99 m (2H), 1.43 s (t-Bu), 2.35-0.72 m (16 H).

Example 22: Phenyl-(2,2,6,6-tetramethyl-piperidin-1-yloxy)-acetonitrile

Analogously to Example 17, 2.45 g (45%) of the title compound are obtained in the form of colourless crystals, m.p. 33-36°C, from 3.15 g (0.02 mol) of 2,2,6,6-tetramethyl-piperidine-1-oxyl, 12 ml (0.1 mol) of benzyl cyanide, 4.2 ml (0.03 mol) of *t*-butyl hydroperoxide (70% in water) and 0.4 ml of the copper(II) chloride solution described in Example 13.

¹H-NMR (300 MHz, CDCl₃): 7.48-7.25 m (5H), 5.55 s (1H), 1.66-1.35 m (6H), 1.45 s (Me), 1.16 s (Me), 1.08 s (Me), 1.00 s (Me).

Example 23: Acetic acid 2-phenyl-2-(2,2,6,6-tetramethyl-piperidin-1-yloxy)-ethyl ester

10 g (0.064 mol) of tetramethyl-piperidine-1-oxyl, 52.6 g (0.32 mol) of 2-phenylethyl acetate, 100 mg of copper(I) bromide, 250 mg of tetrabutylammonium bromide and 16 ml of water are placed in a 350 ml sulfonating flask under nitrogen. With stirring, the mixture is heated to 50°C and then, at 50-55°C, 24.5 g (0.19 mol) of *t*-butyl hydroperoxide (70% in water) are added dropwise in 30 minutes. The mixture is then stirred at 65-70°C until the red nitroxide colour disappears (approximately from 8 to 10 hours). After cooling to 20°C, a solution of 10 g of Na₂S₂O₅ in 50 ml of water is added. After stirring for a further 60 minutes, the organic phase is separated off, washed with 2x50 ml of 20% Na₂CO₃ and 2x50 ml of water and dried over MgSO₄, and the excess 2-phenylethyl acetate is distilled off at 80-90°C under a high vacuum. The solid residue is recrystallised from hexane to yield 8.6 g (42%) of the title compound in the form of white crystals having a melting point of 39-41°C.

Example 24: 2,2-Dimethylpropionic acid 1-(2-acetoxy-1-phenyl-ethoxy)-2,2,6,6-tetramethyl-piperidin-4-yl ester

The title compound is prepared analogously to Example 23. 20.0 g (0.078 mol) of 2,2-dimethyl-propionic acid 2,2,6,6-tetramethyl-piperidin-4-yl ester-1-oxyl are reacted with 64 g (0.39 mol) of 2-phenylethyl acetate and 30 g of *t*-butyl hydroperoxide (70% in water). The crude product is recrystallised from pentane and 17.2 g (53%) of compound 112 are obtained in the form of white crystals having a melting point of 102-103°C.

Example 25: Acetic acid 2-(4-hydroxy-2,2,6,6-tetramethyl-piperidin-1-yloxy)-2-phenylethyl ester

The title compound is prepared analogously to Example 23. 10.0 g (0.058 mol) of 4-hydroxy-2,2,6,6-tetramethyl-piperidine-1-oxyl are reacted with 47.6 g (0.29 mol) of 2-phenylethyl acetate and 16 g of *t*-butyl hydroperoxide (70% in water). The crude product is recrystallised from pentane and 8.4 g (43%) of the title compound are obtained in the form of white crystals having a melting point of 68-69°C.

Example 26: Acetic acid 2-(4-tert-butyl-2,2-diethyl-6,6-dimethyl-3-oxo-piperazin-1-yloxy)-2-phenylethyl ester

The title compound is prepared analogously to Example 23. 10.2 g (0.04 mol) of 4-tert-butyl-2,2-diethyl-6,6-dimethyl-3-oxo-piperazine-1-oxyl are reacted with 32.1 g (0.19 mol) of 2-phenylethyl acetate and 21 g of *t*-butyl hydroperoxide (70% in water). After working up, 14.0 g (85 %) of the crude compound 114 are obtained in the form of a yellow oil.


¹H-NMR (300 MHz, CDCl₃) mixture of diastereoisomers: 7.3-7.1 m (5H Ar), 4.8-4.7 m (1H), 4.6-4.1 m (2H), 3.1-2.8 m (2H), 1.38 s (*t*-Bu), 2.1-0.5 m (28 H).

Example 27: Acetic acid 2-(4-acetylamino-2,2,6,6-tetramethyl-piperidin-1-yloxy)-2-phenylethyl ester

The title compound is prepared analogously to Example 23. 91.4 g (0.43 mol) of 4-acetylamino-2,2,6,6-tetramethyl-piperidine-1-oxyl are reacted with 261 g (1.6 mol) of 2-phenylethyl acetate and 166 g of *t*-butyl hydroperoxide (70% in water). The crude product is dissolved in 500 ml of diethyl ether and then precipitated in 2.5 litres of hexane to yield 119.2 g (74%) of the title compound in the form of white crystals having a melting point of 109-110°C.

WHAT IS CLAIMED IS:

1. Process for the preparation of an amine ether of the formula A





wherein

a is 1 or 2;

when a is 1, E' is E


when a is 2, E' is L;

E is C₁-C₃₆ alkyl; C₃-C₁₈ alkenyl; C₂-C₁₈ alkynyl; C₅-C₁₈ cycloalkyl; C₅-C₁₈ cycloalkenyl; a radical of a saturated or unsaturated aliphatic bicyclic or tricyclic hydrocarbon of 7 to 12 carbon atoms; C₂-C₇alkyl or C₃-C₇alkenyl substituted by halogen, C₁-C₈alkoxy or phenoxy; C₄-C₁₂heterocycloalkyl; C₄-C₁₂heterocycloalkenyl; C₇-C₁₅ aralkyl or C₄-C₁₂heteroaralkyl, each of which is unsubstituted or substituted by C₁-C₄ alkyl or phenyl; or E is a radical of formula (VII) or (VIII)



Ar is C₆-C₁₀aryl or C₅-C₉heteroaryl;

X is phenyl, naphthyl or biphenyl, which is substituted by 1, 2, 3 or 4 D and optionally further substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino;

D is a group , a group C(O)-G₁₃ or a group C(O)-G₉-C(O)-G₁₃;

G₁ and G₂, independently of each other, are hydrogen, halogen, NO₂, cyano,

-CONR₅R₆, -(R₉)COOR₄, -C(O)-R₇, -OR₈, -SR₈, -NHR₈, -N(R₁₈)₂, carbamoyl, di(C₁-C₁₈alkyl)carbamoyl, -C(=NR₅)(NHR₆), C₁-C₁₈alkyl; C₃-C₁₈alkenyl; C₃-C₁₈alkinyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₂-C₁₂heterocycloalkyl; C₁-C₁₈alkyl or C₃-C₁₈alkenyl or C₃-C₁₈alkinyl or C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₂-C₁₂heterocycloalkyl substituted by OH, halogen, NO₂, amino, cyano, carboxy, COOR₂₁, C(O)-R₂₂, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino or a group -O-C(O)-R₇; C₂-C₁₈alkyl which is interrupted by at least one O atom and/or NR₅ group; or are C₆-C₁₀aryl; or phenyl or naphthyl which are substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, halogen, cyano, hydroxy, carboxy, COOR₂₁, C(O)-R₂₂, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or G₁ and G₂ together with the linking carbon atom form a C₃-C₁₂cycloalkyl radical;

G₅ and G₆ are independently of each other H or CH₃;

G₉ is C₁-C₁₂alkylene or a direct bond;

G₁₃ is C₁-C₁₈alkyl;

G₁₄ is C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl, an acyl radical of an aliphatic or unsaturated aliphatic carboxylic or carbamic acid containing 2 to 18 carbon atoms, an acyl radical of a cycloaliphatic carboxylic or carbamic acid containing 7 to 12 carbon atoms, or acyl radical of an aromatic acid containing 7 to 15 carbon atoms;

G₅₅ is H, CH₃ or phenyl;

G₆₆ is -CN or a group of the formula -COOR₄ or -CONR₅R₆ or -CH₂-O-G₁₄;

L is alkylene of 1 to 18 carbon atoms, cycloalkylene of 5 to 8 carbon atoms, cycloalkenylene of 5 to 8 carbon atoms, alkenylene of 3 to 18 carbon atoms, alkylene of 1 to 12 carbon atoms substituted by phenyl or by phenyl substituted by alkyl of 1 to 4 carbon atoms; or is alkylene of 4 to 18 carbon atoms interrupted by COO and/or phenylene;

T' is tertiary C₄-C₁₈alkyl or phenyl, each of which are unsubstituted or substituted by halogen, OH, COOR₂₁ or C(O)-R₂₂; or T' is C₅-C₁₂cycloalkyl; C₅-C₁₂cycloalkyl which is interrupted by at least one O or -NR₁₈-; a polycyclic alkyl radical having 7-18 carbon atoms, or the same radical which is interrupted by at least one O or -NR₁₈-; or T' is -C(G₁)(G₂)-T''; or C₁-C₁₈alkyl

or C₅-C₁₂cycloalkyl substituted by

$$\begin{array}{c} \text{O} \\ \parallel \\ \text{---P---} \begin{array}{l} \text{OR}_{22} \\ \text{OR}_{22} \end{array} \end{array};$$

T'' is hydrogen, halogen, NO₂, cyano, or is a monovalent organic radical comprising 1-50 carbon atoms;

or T" and T' together form a divalent organic linking group completing, together with the hindered amine nitrogen atom and the quaternary carbon atom substituted by G₁ and G₂, an optionally substituted five- or six-membered ring structure;

and

R₄ is hydrogen, C₁-C₁₈alkyl, phenyl, an alkali metal cation or a tetraalkylammonium cation;

R₅ and R₆ are hydrogen, C₁-C₁₈alkyl, C₂-C₁₈alkyl which is substituted by hydroxy or, taken together, form a C₂-C₁₂alkylene bridge or a C₂-C₁₂-alkylene bridge interrupted by O or/and

NR₁₈;

R₇ is hydrogen, C₁-C₁₈alkyl or C₆-C₁₀aryl;

R₈ is hydrogen, C₁-C₁₈alkyl or C₂-C₁₈hydroxyalkyl;

R₉ is C₁-C₁₂alkylene or a direct bond;


R₁₈ is C₁-C₁₈alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, COOR₂₁ or C(O)-R₂₂;

R₂₁ is hydrogen, a alkali metal atom or C₁-C₁₈alkyl; and

R₂₂ is C₁-C₁₈alkyl;

which process comprises

reacting a N-oxyl amine of formula B




with a compound of formula IV or V



in the presence of an organic hydroperoxide and a catalytic amount of copper or a copper compound.

2. Process for the preparation of an amine ether of the formula A according to claim 1

- 70 -




wherein

a is 1 or 2;


when a is 1, E' is E

when a is 2, E' is L;

E is C₁-C₃₆ alkyl; C₃-C₁₈ alkenyl; C₂-C₁₈ alkynyl; C₅-C₁₈ cycloalkyl; C₅-C₁₈ cycloalkenyl; a radical of a saturated or unsaturated aliphatic bicyclic or tricyclic hydrocarbon of 7 to 12 carbon atoms; C₂-C₇alkyl or C₃-C₇alkenyl substituted by halogen; C₇-C₁₅ aralkyl or C₇-C₁₅ aralkyl substituted by C₁-C₄ alkyl or phenyl; or E is a radical of formula (VII)



X is phenyl, naphthyl or biphenyl, which are substituted by 1, 2, 3 or 4 D and optionally further substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino;

D is a group , a group C(O)-G₁₃ or a group C(O)-G₉-C(O)-G₁₃;

G₁ and G₂, independently of each other, are hydrogen, halogen, NO₂, cyano, -CONR₅R₆, -(R₉)COOR₄, -C(O)-R₇, -OR₈, -SR₈, -NHR₈, -N(R₁₈)₂, carbamoyl, di(C₁-C₁₈alkyl)carbamoyl, -C(=NR₅)(NHR₆), C₁-C₁₈alkyl; C₃-C₁₈alkenyl; C₃-C₁₈alkynyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₂-C₁₂heterocycloalkyl; C₁-C₁₈alkyl or C₃-C₁₈alkenyl or C₃-C₁₈alkynyl or C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₂-C₁₂heterocycloalkyl substituted by OH, halogen, NO₂, amino, cyano, carboxy, COOR₂₁, C(O)-R₂₂, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino or a group -O-C(O)-R₇; C₂-C₁₈alkyl which is interrupted by at least one O atom and/or NR₅ group; or are C₆-C₁₀aryl; or phenyl or naphthyl which are substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, halogen, cyano, hydroxy, carboxy,

COOR₂₁, C(O)-R₂₂, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or G₁ and G₂ together with the linking carbon atom form a C₃-C₁₂cycloalkyl radical;

G₅ and G₆ are independently of each other H or CH₃;


G₉ is C₁-C₁₂alkylene or a direct bond;

G₁₃ is C₁-C₁₈alkyl;

L is alkylene of 1 to 18 carbon atoms, cycloalkylene of 5 to 8 carbon atoms, cycloalkenylene of 5 to 8 carbon atoms, alkenylene of 3 to 18 carbon atoms, alkylene of 1 to 12 carbon atoms substituted by phenyl or by phenyl substituted by alkyl of 1 to 4 carbon atoms;

T' is tertiary C₄-C₁₈alkyl or phenyl, each of which are unsubstituted or substituted by halogen, OH, COOR₂₁ or C(O)-R₂₂; or T' is C₅-C₁₂cycloalkyl; C₅-C₁₂cycloalkyl which is interrupted by at least one O or -NR₁₈; a polycyclic alkyl radical having 7-18 carbon atoms, or the same radical which is interrupted by at least one O or -NR₁₈; or T' is -C(G₁)(G₂)-T''; or C₁-C₁₈alkyl

or C₅-C₁₂cycloalkyl substituted by



T'' is hydrogen, halogen, NO₂, cyano, or is a monovalent organic radical comprising 1-50 carbon atoms;

or T'' and T' together form a divalent organic linking group completing, together with the hindered amine nitrogen atom and the quaternary carbon atom substituted by G₁ and G₂, an optionally substituted five- or six-membered ring structure;

and

R₄ is hydrogen, C₁-C₁₈alkyl, phenyl, an alkali metal cation or a tetraalkylammonium cation;

R₅ and R₆ are hydrogen, C₁-C₁₈alkyl, C₂-C₁₈alkyl which is substituted by hydroxy or, taken together, form a C₂-C₁₂alkylene bridge or a C₂-C₁₂-alkylene bridge interrupted by O or/and

NR₁₈;

R₇ is hydrogen, C₁-C₁₈alkyl or C₆-C₁₀aryl;

R₈ is hydrogen, C₁-C₁₈alkyl or C₂-C₁₈hydroxyalkyl;

R₉ is C₁-C₁₂alkylene or a direct bond;

R₁₈ is C₁-C₁₈alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, COOR₂₁ or C(O)-R₂₂;


- 72 -

R_{21} is hydrogen, an alkali metal atom or C_1 - C_{18} alkyl; and

R_{22} is C_1 - C_{18} alkyl;

which process comprises

reacting a N-oxyl amine of formula B





with a hydrocarbon of formula IV or V



in the presence of an organic hydroperoxide and a catalytic amount of copper or a copper compound.

3. Process according to claim 1, wherein the compound of formula A corresponds to formula I or II




wherein


G_1 , G_2 , G_3 and G_4 independently of each other are C_1 - C_{18} alkyl; C_3 - C_{18} alkenyl; C_3 - C_{18} alkinyl; C_1 - C_{18} alkyl or C_3 - C_{18} alkenyl or C_3 - C_{18} alkinyl substituted by OH, halogen or a group $-O-C(O)-R_5$; C_2 - C_{18} alkyl which is interrupted by at least one O atom and/or NR_5 group; or are C_3 - C_{12} cycloalkyl; or C_6 - C_{10} aryl; or G_1 and G_2 and/or G_3 and G_4 together with the linking carbon atom form a C_3 - C_{12} cycloalkyl radical;

a is 1 or 2;

when a is 1, E' is E, wherein E is C_1 - C_{36} alkyl; C_2 - C_{18} alkenyl; C_2 - C_{18} alkynyl; C_5 - C_{18} cycloalkyl; C_5 - C_{18} cycloalkenyl; a radical of a saturated or unsaturated aliphatic bicyclic or tricyclic hydrocarbon of 7 to 12 carbon atoms; C_2 - C_7 alkyl or C_3 - C_7 alkenyl substituted by halogen; C_7 - C_{15} aralkyl or C_7 - C_{15} aralkyl substituted by C_1 - C_4 alkyl or phenyl; or E' is a radical of formula (VII)



X is phenyl, naphthyl or biphenyl, which are substituted by 1, 2, 3 or 4 D and optionally further substituted by NO_2 , halogen, amino, hydroxy, cyano, carboxy, C_1 - C_4 alkoxy, C_1 - C_4 alkylthio, C_1 - C_4 alkylamino or di(C_1 - C_4 alkyl)amino;

D is a group , a group $C(O)-G_{13}$ or a group $C(O)-G_9-C(O)-G_{13}$;

when a is 2, E' is L;

G_5 and G_6 are independently of each other H or CH_3 ;

G_9 is C_1 - C_{12} alkylene or a direct bond;

G_{13} is C_1 - C_{18} alkyl;

L is alkylene of 1 to 18 carbon atoms, cycloalkylene of 5 to 8 carbon atoms, cycloalkenylene of 5 to 8 carbon atoms, alkenylene of 3 to 18 carbon atoms, alkylene of 1 to 12 carbon atoms substituted by phenyl or by phenyl substituted by alkyl of 1 to 4 carbon atoms;


T is a divalent organic radical required to complete formula I to form, together with the hindered amine nitrogen atom and the two quaternary carbon atoms substituted by G_1 and G_2 or G_3 and G_4 , a five- or six-membered ring structure;

T_1 is hydrogen, halogen, NO_2 , cyano, $-(R_9)COOR_4$, $-(R_9)C(O)-R_7$, $-OR_8$, unsubstituted C_1 -

- 74 -

C₁₈alkyl, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₂-C₁₂heterocycloalkyl; or T₁ is C₁-C₁₈alkyl, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₂-C₁₂heterocycloalkyl, which is substituted by NO₂, halogen, hydroxy, cyano, carboxy, C₁-C₆alkanoyl, C₁-C₁₂alkoxy; or phenyl, naphthyl, which are unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, halogen, cyano, hydroxy, carboxy; or T₁ is a residue -CH₂-O-R₁₀ or -CH₂-NR₁₈-R₁₀ or -C(=CH₂)-R₁₁ or -C(=O)-R₁₂;

T₂ is tertiary C₄-C₁₈alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, COOR₂₁ or C(O)-R₂₂; or T₂ is C₅-C₁₂cycloalkyl; C₅-C₁₂cycloalkyl which is interrupted by at least one O; a polycyclic alkyl radical having 7-18 carbon atoms or the same radical which is

interrupted by at least one O atom; or T₂ is -C(G₁)(G₂)-T₁; or  ;

R₄ is hydrogen, C₁-C₁₈alkyl, phenyl, an alkali metal cation or a tetraalkylammonium cation;

R₅ is hydrogen, C₁-C₁₈alkyl or C₆-C₁₀aryl

R₇ is hydrogen, C₁-C₁₈alkyl or phenyl;

R₈ is hydrogen, C₁-C₁₈alkyl or C₂-C₁₈hydroxyalkyl;

R₉ is C₁-C₁₂alkylene or a direct bond;

R₁₀ is hydrogen, formyl, C₂-C₁₈alkylcarbonyl, benzoyl, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl, C₅-C₁₂cycloalkyl interrupted by O or NR₁₈, or is benzyl or phenyl which are unsubstituted or substituted by halogen, OH, COOR₂₁ or C(O)-R₂₂;

R₁₁ is OH, C₁-C₁₈alkoxy, benzyloxy, O-C(O)-(C₁-C₁₈)alkyl, N(R₁₈)₂, or a group C(O)R₂₅;

R₁₂ is OH, O(alkali-metal), C₁-C₁₈alkoxy, benzyloxy, N(R₁₈)₂;

R₁₈ is C₁-C₁₈alkyl or C₂-C₁₈hydroxyalkyl;

R₂₁ is hydrogen, a alkali metal atom or C₁-C₁₈alkyl; and



R₂₂ is C₁-C₁₈alkyl;

R₂₅ is OH, C₁-C₁₈alkoxy, benzyloxy, N(R₁₈)₂;

which process comprises

reacting a N-oxyl hindered amine of formula III or IIIa

- 75 -



with a compound formula IV or V



in the presence of an organic hydroperoxide and a catalytic amount of copper or a copper compound.

4. Process according to claim 1, wherein the organic hydroperoxide used in the process of present invention is a peroxyalcohol containing 3-18 carbon atoms, especially tert.butyl-hydroperoxide.

5. Process according to claim 1, wherein 1 to 100 moles of the compound of formula IV or V, 1 to 20 moles of organic hydroperoxide, and 0.001 mmoles to 0.5 moles of copper catalyst are used per mole of N-oxyl compound of formula B.

6. Process according to claim 1, wherein the compound of formula IV or V is used in excess and serves both as reactant and as solvent for the reaction and/or wherein a further inert organic or inorganic solvent is used.



7. Process according to any of claims 1 to 6, wherein the reaction is carried out in the presence of a phase transfer catalyst.

8. Process according to claim 1, wherein the catalyst is formed from an inorganic Cu(I) or Cu(II) compound dissolved in a suitable solvent.


9. Process according to claim 3, wherein in the formulae I and III

T is an organic linking group containing 2-500 carbon atoms and 0-200 hetero atoms selected from oxygen, phosphorus, sulfur, silicon, halogen and nitrogen as tertiary nitrogen, and forming, together with the carbon atoms it is directly connected to and the nitrogen atom, an optionally substituted, 5-, 6 or 7-membered cyclic ring structure.


10. Process according to any of claims 1-9, wherein the product formed corresponds to one of the formulae



- 77 -



(XIII),



(XIV)

wherein

G_1 , G_2 , G_3 and G_4 independently of each other are C_1 - C_{18} alkyl; C_3 - C_{18} alkenyl; C_3 - C_{18} alkinyl; C_1 - C_{18} alkyl or C_3 - C_{18} alkenyl or C_3 - C_{18} alkinyl substituted by OH, halogen or a group $-O-C(O)-$; R_5 ; C_2 - C_{18} alkyl which is interrupted by O; C_5 - C_{12} cycloalkyl; or phenyl; or G_1 and G_2 and/or G_3 and G_4 together with the linking carbon atom form a C_5 - C_{12} cycloalkyl radical;

Z_1 is O or NR_8 ;

R_8 is hydrogen, OH, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl which are substituted by one or more OH, halogen or a group $-O-C(O)-R_5$, C_2 - C_{18} alkinyl which is substituted by one or more OH, halogen or a group $-O-C(O)-R_5$, C_2 - C_{18} alkyl which is interrupted by at least one O atom and/or NR_5 group, C_3 - C_{12} cycloalkyl or C_6 - C_{10} aryl, C_7 - C_9 phenylalkyl, C_5 - C_{10} heteroaryl, $-C(O)-C_1$ - C_{18} alkyl, $-O-C_1$ - C_{18} alkyl or $-COOC_1$ - C_{18} alkyl;

Q is a direct bond or a divalent radical CR_9R_{10} , $CR_9R_{10}-CR_{11}R_{12}$, $CR_9R_{10}CR_{11}R_{12}CR_{13}R_{14}$, $C(O)$ or $CR_9R_{10}C(O)$;

R_9 , R_{10} , R_{11} , R_{12} , R_{13} and R_{14} are independently hydrogen, phenyl, or C_1 - C_{18} alkyl;


T is $CH_2-C(R_{24})(R_{25})-CH_2$, wherein R_{24} and R_{25} together are $=O$ or independently are H, OH or an organic residue, characterized in that the linking group T in total contains 2-500 carbon atoms and optionally 1-200 hetero atoms selected from, oxygen, phosphorus, sulfur, silicon, halogen and tertiary nitrogen.

- 78 -

11. Process according to claim 3 for the preparation of a compound of formula (I), wherein in the formulae (I)

G_1 , G_2 , G_3 and G_4 , independently of each other, are methyl, ethyl, phenyl or COOR_4 ;

E is a carbon centered radical formed from a C_7 - C_{11} phenylalkane or a C_6 - C_{10} pyridylalkane; or C_5 - C_{12} cycloalkane; or C_5 - C_{12} cycloalkene; or an oxacyclohexane or oxycyclohexene; or C_3 - C_8 alkene; or C_3 - C_8 alkene substituted by phenoxy; or a benzene which is substituted by C_1 - C_4 alkyl and a further substituent selected from C_1 - C_4 alkoxy, glycidyl or glycidyloxy; or E is a radical of formula (VIII)



Ar is C_6 - C_{10} aryl or C_5 - C_9 heteroaryl;

G_{14} is C_1 - C_4 alkyl or an acyl radical of an aliphatic carboxylic acid containing 2 to 4 carbon atoms or benzoyl;

G_{55} is H, CH_3 or phenyl;

G_{66} is $-\text{CN}$ or a group of the formula $-\text{COOR}_4$ or $-\text{CH}_2\text{-O-G}_{14}$;

R_4 is hydrogen or C_1 - C_8 alkyl;

L is a carbon centered radical formed from propane, butane, pentane, 2,2-dimethyl-propane, xylene; and

T is phenylene or an organic linking group of the formula $\begin{array}{c} \text{H}_2 \\ | \\ \text{E}_1 \text{---} \text{C} \text{---} \\ | \\ \text{E}_2 \end{array}$ (VI), wherein





E_2 is $-\text{CO}-$ or $-(\text{CH}_2)_b-$, while b is 0, 1 or 2;

E_1 is a carbon atom carrying the two residues R_{24} and R_{25} , or is $>\text{N-R}_{25}$, or is oxygen, and R_{24} and R_{25} are hydrogen or an organic residue, characterized in that the linking group T in total contains 2-500 carbon atoms and forms, together with the carbon atoms it is directly connected to it and the nitrogen atom, a substituted, 5-, 6 or 7-membered cyclic ring structure, or wherein R_{24} and R_{25} together are $=\text{O}$ or wherein R_{24} is hydrogen and R_{25} is hydrogen or hydroxy;

or E_1 and E_2 together are 1,2-phenylene.

12. Use of an organic hydroperoxide together with a copper catalyst and a compound of formula IV or V as defined in claim 1 for the preparation of a N-hydrocarbyloxy substituted sterically hindered amine from its N-oxyl precursor.

13. A compound of the formula XV, XVI, XVII or XVIII



- 80 -



wherein

G_1 , G_2 and G_{31} are independently methyl or ethyl;

G_3 is C_2 - C_8 alkenyl; C_2 - C_8 alkenyl substituted by phenyl, C_1 - C_4 alkyl-phenyl, cyclohexyl, C_1 - C_4 alkyl-cyclohexyl or $COX'G_8$; or G_3 is OG_{10} ; or is a carbon-bonded 5- or 6-membered unsubstituted or alkyl substituted heterocyclic residue containing 3-12 carbon atoms in total and whose heteroatoms are selected from nitrogen and oxygen;

G_4 is as defined for G_3 or is C_1 - C_{18} alkyl, provided that G_4 is not methyl when G_3 is C_2 -alkenyl; or G_3 and G_4 together with the carbon atom they are attached to form the residue Ph-CH-CN, or form a carbon-bonded 5- or 6-membered unsubstituted or alkyl substituted, unsaturated heterocyclic residue containing 3-12 carbon atoms in total, whose heteroatoms are selected from nitrogen and oxygen;

G_6 is H; OH; OR_3 ; NR_4R_5 ; $(CO)R_6$; or is a radical of formula



G_7 is H;



or G_6 and G_7 together are $=O$ or a residue of formula $-O-CH_2-C(R_1)(R_2)-(CH_2)_m-O-$;

G_8 is hydrogen or C_1 - C_8 alkyl or C_2 - C_8 hydroxyalkyl;

G'_8 is hydrogen or C_1 - C_8 alkyl or C_2 - C_8 hydroxyalkyl or C_2 - C_8 alkenyl; G_{10} is C_1 - C_{18} alkyl; C_1 - C_{18} alkyl substituted by phenyl or C_1 - C_{12} alkyl, C_1 - C_{12} alkoxy and/or OH substituted phenyl; phenyl substituted by C_1 - C_{12} alkyl, C_1 - C_{12} alkoxy, OH; or is a carbon-bonded 5- or 6-membered unsubstituted or alkyl substituted heterocyclic residue containing 3-12 carbon atoms and whose heteroatoms are selected from nitrogen and oxygen;

G_{15} is H or methyl;

G₁₆ is OH, OR₃, NR₄R₅, (CO)R₆, or is a radical of formula



G₁₇ is H;

or G₁₆ and G₁₇ together are =O or a residue of formula -O-CH₂-C(R₁)(R₂)-(CH₂)_m-O-;

G₁₈ is H or methyl or =O;

G₂₀ is H, C₁-C₁₈alkyl or C₅-C₁₂cycloalkyl;

G₂₁ and G₂₂ are independently hydrogen, halogen, C₁-C₁₂alkyl or C₁-C₁₂alkoxy;

G₂₃ is oxyl, OH or OE, where E is as defined in claim 1;

G₂₄ is methyl, ethyl or phenyl;

Ph is phenyl or phenyl substituted by C₁-C₄alkyl, C₁-C₄alkoxy, halogen and/or nitro;

m is 0 or 1;

R₁ is hydrogen, C₁-C₄alkyl, hydroxyl or hydroxymethyl;

R₂ is hydrogen, alkyl of 1 to 12 carbon atoms or alkenyl of 2 to 12 carbon atoms;

R₃ is alkyl of 1 to 18 carbon atoms, alkoxycarbonylalkylenecarbonyl of 4 to 18 carbon atoms, alkenyl of 2 to 18 carbon atoms, glycidyl, 2,3-dihydroxypropyl, 2-hydroxy or 2-

(hydroxymethyl) substituted alkyl of 3 to 12 carbon atoms which alkyl is interrupted by

oxygen, an acyl radical of an aliphatic or unsaturated aliphatic carboxylic or carbamic acid

containing 2 to 18 carbon atoms, an acyl radical of a cycloaliphatic carboxylic or carbamic

acid containing 7 to 12 carbon atoms, or acyl radical of an aromatic acid containing 7 to 15

carbon atoms;

R₄ is hydrogen, alkyl of 1 to 18 carbon atoms or acyl of 2 to 6 carbon atoms;

R₅ is hydrogen, alkyl of 1 to 18 carbon atoms, an acyl radical of an aliphatic or unsaturated

aliphatic carboxylic or carbamic acid containing 2 to 18 carbon atoms, an acyl radical of a

cycloaliphatic carboxylic or carbamic acid containing 7 to 12 carbon atoms, an acyl radical of

an aromatic carboxylic acid containing 7 to 15 carbon atoms, or R₄ and R₅ together are -

(CH₂)₅CO-, phthaloyl or a divalent acyl radical of maleic acid;

R₆ is alkoxy of 1 to 18 carbon atoms, alkenyloxy of 2 to 18 carbon atoms, -NHalkyl of 1 to 18 carbon atoms or -N(alkyl)₂ of 2 to 36 carbon atoms;

R₇ and R₈ are independently chlorine, alkoxy of 1 to 18 carbon atoms, amino substituted by 2-hydroxyethyl, -NH(alkyl) of 1 to 18 carbon atoms, or -N(alkyl)₂ of 2 to 36 carbon atoms;

R₉ is oxygen, or R₉ is nitrogen substituted by hydrogen or alkyl of 1 to 12 carbon atoms;

R₁₃ is silyl or silyloxy substituted three times independently by hydrogen, by phenyl, by alkyl of 1 to 4 carbon atoms or by alkoxy of 1 to 4 carbon atoms;

R₃₀ is H, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl, C₃-C₁₈alkoxyalkyl;

X' is O or NG₈ ;

Y-Z is >C(G₁₇)G₁₆ or O or >N-R₃₀.

14. Use of a compound of formula XV, XVI, XVII and/or XVIII according to claim 13 as stabilizer for organic material against degradation by light, oxygen and/or heat or as flame retardant.

15. Process for flame retarding or stabilizing an organic material against degradation by light, oxygen and/or heat, which process comprises applying or incorporating an amine ether into said material, characterized in that the amine ether is a compound of the formula XV, XVI, XVII and/or XVIII according to claim 13.

16. Composition comprising

- A) an organic material which is sensitive to oxidative, thermal and/or actinic degradation, and
- B) as stabilizer at least one compound of the formula XV, XVI, XVII and/or XVIII according to claim 13.

17. Use of a compound of formula XV, XVI, XVII and/or XVIII according to claim 13 as polymerization regulator.

18. A polymerizable composition, comprising

- a) at least one ethylenically unsaturated monomer or oligomer, and
- b) as polymerization regulator at least one compound of XV, XVI, XVII and/or XVIII according to claim 13.

19. A composition according to claim 18, wherein the ethylenically unsaturated monomer or oligomer is selected from the group consisting of ethylene, propylene, n-butylene, i-butylene, styrene, substituted styrene, conjugated dienes, acrolein, vinyl acetate, vinylpyrrolidone, vinylimidazole, maleic anhydride, (alkyl)acrylic acidanhydrides, (alkyl)acrylic acid salts, (alkyl)acrylic esters, (meth)acrylonitriles, (alkyl)acrylamides, vinyl halides or vinylidene halides.

- 82 -

R₆ is alkoxy of 1 to 18 carbon atoms, alkenyloxy of 2 to 18 carbon atoms, -NHalkyl of 1 to 18 carbon atoms or -N(alkyl)₂ of 2 to 36 carbon atoms;

R₇ and R₈ are independently chlorine, alkoxy of 1 to 18 carbon atoms, amino substituted by 2-hydroxyethyl, -NH(alkyl) of 1 to 18 carbon atoms, or -N(alkyl)₂ of 2 to 36 carbon atoms;

R₉ is oxygen, or R₉ is nitrogen substituted by hydrogen or alkyl of 1 to 12 carbon atoms;

R₁₃ is silyl or silyloxy substituted three times independently by hydrogen, by phenyl, by alkyl of 1 to 4 carbon atoms or by alkoxy of 1 to 4 carbon atoms;

R₃₀ is H, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl, C₃-C₁₆alkoxyalkyl;

X' is O or NG₈;

Y-Z is >C(G₁₇)G₁₆ or O or >N-R₃₀.

14. Use of a compound of formula XV, XVI, XVII and/or XVIII according to claim 13 as stabilizer for organic material against degradation by light, oxygen and/or heat or as flame retardant.

15. Process for flame retarding or stabilizing an organic material against degradation by light, oxygen and/or heat, which process comprises applying or incorporating an amine ether into said material, characterized in that the amine ether is a compound of the formula XV, XVI, XVII and/or XVIII according to claim 13.

16. Composition comprising

- A) an organic material which is sensitive to oxidative, thermal and/or actinic degradation, and
- B) as stabilizer at least one compound of the formula XV, XVI, XVII and/or XVIII according to claim 13.

17. Use of a compound of formula XV, XVI, XVII and/or XVIII according to claim 13 as polymerization regulator.

18. A polymerizable composition, comprising

- a) at least one ethylenically unsaturated monomer or oligomer, and
- b) as polymerization regulator at least one compound of XV, XVI, XVII and/or XVIII according to claim 13.

19. A composition according to claim 18, wherein the ethylenically unsaturated monomer or oligomer is selected from the group consisting of ethylene, propylene, n-butylene, i-butylene, styrene, substituted styrene, conjugated dienes, acrolein, vinyl acetate, vinylpyrrolidone, vinylimidazole, maleic anhydride, (alkyl)acrylic acidanhydrides, (alkyl)acrylic acid salts, (alkyl)acrylic esters, (meth)acrylonitriles, (alkyl)acrylamides, vinyl halides or vinylidene halides.

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
6 December 2001 (06.12.2001)

PCT

(10) International Publication Number
WO 01/92228 A3(51) International Patent Classification⁷: C07D 211/94,
405/12, 401/12, C08K 5/3435, C08F 4/00, C07D 217/26,
209/44, 241/08(74) Common Representative: CIBA SPECIALTY CHEM-
ICALS HOLDING INC.: Klybeckstrasse 141, CH-4057
Basel (CH).

(21) International Application Number: PCT/EP01/05668

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK,
SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA,
ZW.

(22) International Filing Date: 17 May 2001 (17.05.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00810461.4 26 May 2000 (26.05.2000) EP(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and


(75) Inventors/Applicants (*for US only*): HAFNER, Andreas
[CH/CH]: Balkenweg 23, CH-4460 Gelterkinden (CH).
KIRNER, Hans, Jürg [DE/CH]: Wartenbergstrasse 35,
CH-4133 Pratteln (CH). SCHWARZENBACH, Franz
[CH/CH]: Neufeldstrasse 11, CH-4402 Frenkendorf
(CH). VAN DER SCHAAF, Paul, Adriaan [NL/CH]:
Marssstrasse 17, CH-4123 Allschwil (CH). NESVADBA,
Peter [CH/CH]: Route des Pralettes 83A, CH-1723 Marly
(CH).

Published:

— with international search report

(88) Date of publication of the international search report:
16 May 2002For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR THE SYNTHESIS OF AMINE ETHERS FROM SECONDARY AMINO OXIDES

(57) Abstract: An amine ether of formula (A) wherein a is 1 or 2; and when a is 1, E is E'; when a is 2, E is L; E' is C₁-C₃₆ alkyl; C₃-C₁₈ alkenyl; C₂-C₁₈ alkynyl; C₅-C₁₈ cycloalkyl; C₅-C₁₈ cycloalkenyl; a radical of a saturated or unsaturated aliphatic bicyclic or tricyclic hydrocarbon of 7 to 12 carbon atoms; C₂-C₇alkyl or C₃-C₇alkenyl substituted by halogen; C₇-C₁₅aralkyl or C₇-C₁₅ aralkyl substituted by C₁-C₄ alkyl or phenyl; or E' is a radical of formula (VII) as explained in claim 1; T' is tertiary C₄-C₁₈alkyl or phenyl, each of which are unsubstituted or substituted by halogen, OH, COOR₂₁ or C(O)-R₂₂; or T' is C₅-C₁₂cycloalkyl; C₅-C₁₂cycloalkyl which is interrupted by at least one O or -NR₁₈; a polycyclic alkyl radical having 7-18 carbon atoms, or the same radical which is interruptedby at least one O or -NR₁₈; or T' is -C(G₁)(G₂)-T''; or C₁-C₁₈alkyl or C₅-C₁₂cycloalkyl substituted by F(I)T'' is hydrogen, halogen, NO₂, cyano, or is a monovalent organic radical comprising 1-50 carbon atoms; or T'' and T' together form a divalent organic linking group completing, together with the hindered amine nitrogen atom and the quaternary carbon atom substituted by G₁ and G₂, an optionally substituted five- or six-membered ring structure; and all other residues are as defined in claim 1, are obtained in good yield from the corresponding N-oxyl hindered amine precursor by reaction with a hydrocarbon E₁-H or H-L-H in the presence of an organic hydroperoxide and a catalytic amount of copper or a copper compound. The products of present process find utility as polymerization regulators and/or light stabilizers for organic material.

WO 01/92228 A3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/05668

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C07D211/94 C07D405/12 C07D401/12 C08K5/3435 C08F4/00
C07D217/26 C07D209/44 C07D241/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C07D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

BEILSTEIN Data, EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category * Citation of document, with indication, where appropriate, of the relevant passages

Relevant to claim No.

Y US 4 921 962 A (GALBO J.P. & ACKERMAN
M.H.) 1 May 1990 (1990-05-01)
cited in the application
claim 1; examples 5,12,22,24,25

Y CONNOLLY T.J. ET AL.: "Photochemical
synthesis of TEMPO-capped initiators for
"living" free radical polymerization"
TETRAHEDRON LETTERS, NL, ELSEVIER SCIENCE
PUBLISHERS, AMSTERDAM,
vol. 37, no. 28, 8 July 1996 (1996-07-08),
pages 4919-4922, XP004029548
ISSN: 0040-4039
the whole document

-/--

1-12

1-12



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"g" document member of the same patent family

Date of the actual completion of the international search

8 November 2001

Date of mailing of the international search report

22.01.02

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Fink, D

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 01/05668

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 99 46261 A (CIBA SPECIALITY CHEMICALS HOLDING INC.) 16 September 1999 (1999-09-16) examples A1-A25 ---	1-12
X	DE 199 07 945 A (CIBA GEIGY AG) 26 August 1999 (1999-08-26) page 5, line 23 - line 59 page 19, line 27 - line 29 ---	13
A	EP 0 569 334 A (CIBA-GEIGY AG) 10 November 1993 (1993-11-10) claims 1,4,6; example 19 -----	1-12

INTERNATIONAL SEARCH REPORT

International application No.
PCT/EP 01/05668

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

1 - 12

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. Claims: 1-12

the process for the preparation of known N-hydrocarbyloxy substituted sterically hindered amines

2. Claims: 13-19 (all in part)

the N-hydrocarbyloxy substituted sterically hindered amines of the formulae (XV) according to the present claim 13

3. Claims: 13-19 (all in part)

the N-hydrocarbyloxy substituted sterically hindered amines of the formulae (XVI) according to the present claim 13

4. Claims: 13-19 (all in part)

the N-oxy substituted sterically hindered amines of the formulae (XVII) according to the present claim 13

5. Claims: 13-19 (all in part)

the N-oxy substituted sterically hindered amines of the formulae (XVIII) according to the present claim 13

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/05668

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4921962	A	01-05-1990	NONE	
WO 9946261	A	16-09-1999	AT 38799 A AU 1863699 A AU 2929699 A BE 1012399 A3 BR 9900977 A CN 1228424 A CZ 9900789 A3 DE 19909767 A1 WO 9946261 A1 EP 1071681 A1 ES 2155014 A1 FR 2777892 A1 GB 2335190 A ,B JP 11322714 A NL 1011493 C2 NL 1011493 A1	15-06-2001 23-09-1999 27-09-1999 03-10-2000 21-03-2000 15-09-1999 15-09-1999 16-09-1999 16-09-1999 31-01-2001 16-04-2001 29-10-1999 15-09-1999 24-11-1999 28-10-1999 10-09-1999
DE 19907945	A	26-08-1999	IT M1980366 A1 BR 9900807 A CN 1235159 A DE 19907945 A1 ES 2159462 A1 FR 2777004 A1 GB 2334717 A ,B JP 11315067 A NL 1011394 C2 NL 1011394 A1 SG 74700 A1 US 6117995 A IT M1990377 A1	25-08-1999 28-03-2000 17-11-1999 26-08-1999 01-10-2001 08-10-1999 01-09-1999 16-11-1999 26-10-1999 26-08-1999 22-08-2000 12-09-2000 27-12-1999
EP 0569334	A	10-11-1993	US 5374729 A CA 2095576 A1 DE 69300062 D1 DE 69300062 T2 EP 0569334 A1 JP 3211041 B2 JP 6041077 A MX 9302589 A1	20-12-1994 08-11-1993 23-03-1995 22-06-1995 10-11-1993 25-09-2001 15-02-1994 01-11-1993